敬业（营口）中板有限公司
JINGYE (YINGKOU) MEDIUM PLATE CO.LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE

订货单位 PURCHASER	CUMIC STEEL USA, INC	产品名称 PRODUCT	普通碳素结构钢 General carbon structural steel		
收货单位 CONSIGNEE	CUMIC STEEL USA, INC	合同编号 CONTRACT NO.	YGCAZANN250983002-01		
技术标准/牌号 SPEC/GRADE	ASTM A36/A36M;ASTM A36	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20251012
		证明书编号 CERTIFICATE NO.	251012Z00913	是否保性能 GUARANTEE OR NOT	是 YES
车 号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS % C	Si	Mn	P	S	CEV	Cr	Mo	V	Ni	Cu	Nb	Ti	B 0A01 屈服强度 MPa Rp0.2	B 0A02 抗拉强度 MPa Rm	B 0A03 断后伸长率 % B5	B 0A04 屈强比	B 0B01 弯曲试验 d=3a 180°	A 0C01 冲击单值A J	A 0C012 冲击单值B J	A 0C013 冲击单值C J	A 0C02 冲击均值 Ave J
							×10⁻³	×10⁻³	×10⁻³	×10⁻⁴	×10⁻⁴	×10⁻²	×10⁻³	×10⁻⁴	×10⁻³	×10⁻⁴	×10⁻³	×10⁻⁴	×10⁻⁴										
25119721A	S5A100153	S5A12066101	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12066201	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12066301	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12067101	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12067201	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12067301	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12068101	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12068201	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12068301	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12069101	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12069201	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
25119721A	S5A100153	S5A12069301	8x2440x12000	1	1,839	L	131	163	838	240	139	29	103	20	1	330	10	30	30	300	450	30	0.67	OK	107	75	88	90
			合计(TOTAL):	12	22,068																							

注释 NOTES

L：熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACTTEST：20°C，纵向LONGITUDINAL，近表 CLOSE TO SURFACE，尺寸SIZE10*5*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PRECENTAGE ELONGATION AFTER FRACTURE
B0A04=YIELD STRENGTH RATIO
B0B01=BENDTEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

本产品已按照标准要求进行制造和检验，其结果符合要求，目视及尺寸检验均符合标准要求，特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIR EMENTS OF THE ABOVE MATERIAL SPECIFICATION Both BOTH VISUAL AND DIMENSIONAL INSPECTION MEET THE STANDARD REQUIREMENTS

技术中心
Technology Center