



日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE



订货单位 PURCHASER	SAMSUNG C&T CORPORATION	产品名称 PRODUCT	普通碳素结构钢 General carbon structural steel		
收货单位 CONSIGNEE	SAMSUNG C&T CORPORATION	合同编号 CONTRACT NO.	YGCAZANN0241283001-02		
技术标准/牌号 SPEC/GRADE	ASTM A36/A36M-2019 ; ASTM A36	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20250117
		证明书编号 CERTIFICATE NO.	250117Z00169		
车号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析 区域 AA	化学成分 CHEMICAL ANALYSIS %														B 0A01	B 0A02	B 0A03	B 0A04	B 0B01	A 0C01	A 0C012	A 0C013	A 0C02
							C	Si	Mn	P	S	CEV	Cr	Mo	V	Ni	Cu	Nb	Ti	屈服 强度	抗 拉 强度	断后 伸 长 率	屈 强 比	弯 曲 试 验	冲 击 单 值 A	冲 击 单 值 B	冲 击 单 值 C	冲 击 均 值 Ave	
							x10 ⁻³	x10 ⁻³	x10 ⁻³	x10 ⁻⁴	x10 ⁻⁴	x10 ⁻²	x10 ⁻³	x10 ⁻⁴	x10 ⁻⁴	MPa	MPa	%		d=3a	J	J	J						
25101156C	2514163	25A5408024	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408025	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408026	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408027	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408028	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408029	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408030	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408031	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408032	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408033	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
25101156C	2514163	25A5408034	12x2440x12000	1	2,758	L	125	174	821	300	63	27	25	20	1	80	9	40	30	315	474	25.5	0.66	OK	127	148	129	135	
合计(TOTAL):				11	30,338																								

注释 NOTES	L : 熔炼成分 SMELTING COMPOSITION 拉伸标距(GAUGE LENGTH) Lo=200 mm A0C冲击试验IMPACTTEST : 20 ,纵向LONGITUDINAL , 近表 CLOSE TO SURFACE , 尺寸SIZE10*10*55 B0A01=YIELD STRENGTH B0A02=TENSILE STRENGTH B0A03=PERCENTAGE ELONGATION AFTER FRACTURE	B0A04=YIELD STRENGTH RATIO B0B01=BENDTEST A0C01=IMPACT TEST A A0C012=IMPACT TEST B A0C013=IMPACT TEST C A0C02=IMPACT AVERAGE
	According to EN 10204 3.1	

	本产品已按照标准要求进行制造和检验,其结果符合要求,特此证明。 WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION	冶金技术处处长 DIRECTOR OF METALLURGICAL DEPARTMENT