

XINGHAN

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD.

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

产品质量证明书

MILL'S TEST CERTIFICATE

订货单位 CUSTOMER		CUMIC STEEL LIMITED								钢号 GR.37	产品名称 PRODUCT					GALVALUME STEEL CORRUGATED SHEETS		
收货单位 PURCHASER		CUMIC STEEL LIMITED									签发日期 OF ISSUE		DATE			2024.8.10		
标准 SPECIFICATION		ASTM A792M									合同号 NO.					CONTRACT		ZG202405172977
捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{eL} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
508	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
532	0.955	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
533	0.97	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	660	670	3	92
534	0.972	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	93
536	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	655	665	4	92
537	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	93
538	0.972	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	665	665	4	92
539	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
540	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	665	665	4	93
541	0.973	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	660	670	3	92
542	0.978	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	670	3	93
544	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	655	665	4	92
549	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	660	665	3	92
555	0.979	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	665	665	4	93
559	0.974	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	92
560	0.97	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	660	665	3	92
561	0.959	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	665	665	4	93
583	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.032	0.22	0.008	0.009	0.04	660	670	3	92
584	0.961	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	660	670	3	93
586	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.21	0.009	0.009	0.04	655	665	4	92
593	0.975	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	660	670	3	93
597	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	665	665	4	92
598	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	665	3	92
601	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.22	0.008	0.009	0.04	665	665	4	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
604	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	670	3	92
605	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	660	670	3	93
531	0.961	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.21	0.009	0.009	0.04	655	665	4	92
535	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	665	3	92
543	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
547	0.978	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
553	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
554	0.969	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
556	0.97	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
557	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
558	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
585	0.96	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
591	0.969	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
607	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
562	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
609	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
525	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
589	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
603	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
551	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
587	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
599	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
602	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
595	0.974	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
545	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
606	0.955	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
579	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
500	0.969	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
501	0.974	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
502	0.975	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
503	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	670	3	92
504	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	660	670	3	93
505	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	655	665	4	92
506	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	665	4	92
507	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	665	665	4	93
509	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.22	0.008	0.009	0.04	660	670	3	92
510	0.96	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	660	665	3	92



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size(mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
511	0.96	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	665	665	4	93
513	0.958	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	92
515	0.957	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	660	670	3	93
516	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	655	665	4	92
517	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	660	670	3	93
519	0.959	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	665	665	4	92
520	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	660	665	3	92
521	0.954	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	665	665	4	93
523	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	660	670	3	92
524	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	660	670	3	93
526	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	655	665	4	92
527	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
528	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
530	0.96	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.21	0.009	0.009	0.04	660	670	3	92
564	0.958	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.031	0.25	0.007	0.01	0.04	660	665	3	92
566	0.955	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	665	665	4	93
568	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.03	0.22	0.008	0.008	0.04	660	670	3	92
570	0.96	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	670	3	93
573	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
575	0.964	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	93
577	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	665	665	4	92
578	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	665	3	92
581	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.031	0.25	0.007	0.01	0.04	665	665	4	93
582	0.963	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	670	3	92
590	0.959	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	670	3	93
594	0.974	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	655	665	4	92
608	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.035	0.26	0.008	0.009	0.04	660	665	3	92
512	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	665	665	4	93
514	0.958	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.033	0.23	0.008	0.009	0.04	660	670	3	92
518	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	665	3	92
529	0.969	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	665	665	4	93
563	0.957	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.035	0.26	0.008	0.009	0.04	660	670	3	92
565	0.955	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.03	0.22	0.008	0.008	0.04	660	670	3	93
567	0.96	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	655	665	4	92
569	0.961	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.22	0.008	0.009	0.04	660	670	3	93
610	1.402	294	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	665	665	4	92
600	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.21	0.009	0.009	0.04	660	665	3	92



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{eL} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
596	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.21	0.009	0.009	0.04	665	665	4	93
592	0.974	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	102	0.031	0.25	0.007	0.01	0.04	660	670	3	92
588	0.968	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	660	670	3	93
580	0.966	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	109	0.032	0.22	0.008	0.009	0.04	655	665	4	92
576	0.97	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	660	665	3	92
574	0.969	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.21	0.009	0.009	0.04	665	665	4	93
572	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	660	670	3	92
571	0.962	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	660	665	3	92
552	0.959	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	665	665	4	93
550	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.22	0.008	0.009	0.04	660	670	3	92
548	0.967	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	670	3	93
522	0.965	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	655	665	4	92
546	0.961	200	0.33*851*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.21	0.009	0.009	0.04	660	670	3	93
796	1.193	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
691	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
669	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
686	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
651	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
672	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
683	1.208	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
771	1.217	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
756	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
752	1.209	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
748	1.197	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
745	1.209	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
737	1.196	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
735	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
723	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
711	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
707	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
659	1.196	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
655	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
664	1.206	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
678	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
685	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
689	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
770	1.209	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665 (2)	4	92



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
790	1.209	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
794	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
650	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
652	1.208	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
662	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
675	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
676	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
682	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
695	1.206	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
795	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
799	1.218	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
658	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
661	1.196	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
699	1.21	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
700	1.207	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
703	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
704	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
708	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
710	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
712	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
714	1.197	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
715	1.196	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
716	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
718	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
719	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
721	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
724	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
727	1.21	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
728	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
730	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
732	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
733	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
736	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
738	1.206	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
742	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	3	92
744	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
749	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
753	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
757	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
766	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
767	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
768	1.207	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
774	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
777	1.193	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
778	1.197	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
779	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
781	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
782	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
783	1.209	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
784	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
785	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
786	1.22	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
787	1.185	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
788	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
797	1.194	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
804	1.227	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
805	1.21	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
660	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
701	1.213	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
705	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
709	1.212	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
713	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
717	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
725	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
734	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
739	1.196	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
741	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
743	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
746	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
747	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
750	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
751	1.196	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
754	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
758	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
760	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
775	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
780	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
806	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
807	0.678	110	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
720	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
762	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
765	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
803	1.222	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
690	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
722	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
726	1.197	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
729	1.207	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
740	1.208	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
755	1.216	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
759	1.213	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
764	1.215	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
801	1.195	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
731	1.197	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
681	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
772	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
688	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
668	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
696	1.2	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
677	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
674	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
763	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
673	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
679	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
680	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
671	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
793	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
802	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
769	1.206	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
693	1.207	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
694	1.207	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
665	1.208	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
666	1.208	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
773	1.208	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
663	1.209	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
684	1.211	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
702	1.215	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
776	1.216	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
798	1.216	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
792	1.222	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
653	1.206	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
657	1.204	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
687	1.195	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
698	1.198	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
706	1.199	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
761	1.212	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
791	1.211	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
800	1.214	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
667	1.215	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
670	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
692	1.202	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
789	1.209	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
654	1.203	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
656	1.205	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
697	1.201	200	0.33*851*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
859	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
635	1.451	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
817	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
833	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
848	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
857	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
877	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
890	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
891	1.433	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
892	1.448	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
894	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
910	1.457	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
911	1.426	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
915	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
932	1.442	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
933	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
934	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
941	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
944	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
948	1.433	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
611	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
613	1.458	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
615	1.448	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
617	1.44	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
619	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
621	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
623	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
625	1.453	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
640	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
644	1.447	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
645	1.446	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
648	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
649	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
808	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
815	1.45	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
820	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
826	1.44	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
830	1.432	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
838	1.448	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
849	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
853	1.431	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
855	1.447	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
858	1.446	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
861	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
863	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
867	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	3	92
874	1.446	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
876	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
881	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
882	1.442	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	3	93
883	1.442	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
884	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
909	1.419	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
895	1.428	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
937	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
810	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
836	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
914	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
940	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
879	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
936	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
813	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
898	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
816	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
889	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
812	1.442	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
637	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
632	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
638	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
639	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
887	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
865	1.445	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
905	1.445	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
646	1.449	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
612	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
614	1.457	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
616	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
620	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
622	1.433	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
624	1.45	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
626	1.449	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
627	1.45	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
628	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
629	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
630	1.451	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
835	1.43	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
850	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
852	1.432	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
854	1.455	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
631	1.411	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
633	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
634	1.432	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
636	1.458	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
641	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
642	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
809	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
811	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
818	1.44	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
819	1.44	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
822	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
823	1.453	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
825	1.442	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
827	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
829	1.442	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
831	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
834	1.431	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
837	1.445	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
840	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
842	1.451	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
844	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
846	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
851	1.44	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
856	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
860	1.433	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
862	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
864	1.431	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
868	1.431	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
870	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
872	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
875	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
878	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
839	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
841	1.451	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
843	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
845	1.432	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%)			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{eL} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
866	1.45	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
871	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
873	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
880	1.427	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
888	1.429	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
897	1.426	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
900	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
901	1.441	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
904	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
907	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
908	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
913	1.456	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
916	1.456	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
917	1.432	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
918	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
919	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
920	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
921	1.446	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
922	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
923	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
926	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
927	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
930	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
931	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
939	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
943	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
947	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
951	0.897	123	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
643	1.449	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
647	1.45	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
814	1.439	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
824	1.438	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	4	92
828	1.448	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
832	1.435	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
847	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
893	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
896	1.426	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size(mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass(g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
899	1.44	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
902	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
903	1.422	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
906	1.454	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
912	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
924	1.445	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
925	1.449	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
928	1.446	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
929	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
938	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
942	1.44	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
945	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
946	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
949	1.437	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
950	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
869	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
618	1.436	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
821	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
885	1.444	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
886	1.443	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
935	1.434	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1138	1.741	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1147	1.745	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1069	1.747	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
1136	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
1142	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1161	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1130	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1104	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1115	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1101	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1100	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
988	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1067	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1017	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1149	1.758	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1061	1.758	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1140	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1102	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
975	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1134	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1132	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1131	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1128	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1119	1.772	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1064	1.773	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1009	1.747	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1039	1.739	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1146	1.744	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1229	1.747	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
1240	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
1159	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1160	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1141	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1125	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1099	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1095	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1077	1.758	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1157	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1221	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1122	1.763	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1127	1.769	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1205	1.77	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1223	1.739	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1114	1.744	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1055	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1135	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
995	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1103	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	4	92
987	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1148	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1139	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1137	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1143	1.774	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size(mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass(g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A(%)	HRB
985	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1012	1.758	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
996	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
1079	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1113	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1213	1.769	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1144	1.742	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1063	1.746	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1204	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1068	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1222	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1062	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1094	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1117	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1201	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1065	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1203	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1239	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1215	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1066	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1220	1.763	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
962	1.765	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1060	1.766	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1181	1.767	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1207	1.776	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1085	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
984	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
993	1.738	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
1074	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
999	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1174	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1033	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	4	92
1037	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1045	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1070	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1088	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1049	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1057	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
968	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
967	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1243	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1021	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1092	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1076	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1083	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1029	1.758	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1217	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1081	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
961	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1087	1.768	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1073	1.771	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1072	1.772	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1053	1.774	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
986	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
970	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
960	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1004	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1032	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
966	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1014	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1096	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
969	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1013	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1041	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1028	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
964	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1052	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1036	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1048	1.77	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1212	1.771	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1084	1.771	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1245	1.773	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1056	1.78	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	4	92
1214	1.781	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1249	2.311	266	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1080	1.745	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1105	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1027	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1098	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1018	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
1016	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
1171	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1197	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1006	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1177	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1191	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1199	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1183	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1015	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
954	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
974	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1086	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1216	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1234	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
965	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1193	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
963	1.758	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1156	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1230	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1020	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1233	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1244	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1180	1.765	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1184	1.768	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1007	1.783	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1107	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
1187	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
1228	1.745	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
971	1.747	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1232	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1176	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1179	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1202	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1155	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1173	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1121	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1145	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1090	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1169	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1200	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1196	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1206	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1209	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1246	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1040	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1124	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1153	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1133	1.763	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1026	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1241	1.765	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1198	1.767	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1151	1.769	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
1082	1.77	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
1185	1.778	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1050	1.745	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1167	1.745	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
982	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
992	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
953	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1238	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1075	1.766	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
977	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1150	1.779	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1154	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1168	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1175	1.758	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1182	1.76	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1186	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size(mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass(g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{eL} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
1190	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1192	1.77	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1008	1.776	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1019	1.781	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1165	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1042	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1059	1.729	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
991	1.739	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1236	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1189	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	93
955	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92
1058	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1152	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1003	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1044	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1178	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1111	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1078	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1208	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1002	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1129	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1242	1.767	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
978	1.771	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1158	1.784	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1248	1.769	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1224	1.737	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
983	1.744	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1164	1.747	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
980	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1163	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1235	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1211	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	660	670	3	92
973	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	660	665	3	92
979	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	665	665	4	93
972	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1001	1.755	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	660	670	3	92
1195	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	655	665	4	92



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size(mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass(g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1000	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1225	1.757	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	92
1247	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	660	665	3	92
958	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	665	665	4	93
997	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1162	1.762	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1218	1.763	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1219	1.765	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1210	1.768	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1166	1.774	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1194	1.777	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
952	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1022	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1023	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	660	670	3	93
1024	1.763	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1025	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1030	1.76	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	665	665	4	92
1038	1.759	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1043	1.753	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	665	665	4	93
1046	1.786	200	0.33*851*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1054	1.765	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1071	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	665	665	4	92
990	1.744	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	665	3	92
1089	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	665	665	4	93
1097	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	660	670	3	92
1108	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	660	670	3	93
1109	1.77	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	655	665	4	92
1116	1.764	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1170	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	665	665	4	93
1172	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	660	670	3	92
1188	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	660	665	3	92
1227	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	665	665	4	93
1231	1.749	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1005	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	660	670	3	93
1237	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	655	665	4	92
1011	1.747	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1034	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	665	665	4	92

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1051	1.748	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1123	1.752	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1118	1.753	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1093	1.754	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1031	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1091	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1106	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1112	1.756	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.035	0.26	0.008	0.009	0.04	660	670	3	92
1226	1.759	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1047	1.763	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	665	665	4	93
1126	1.769	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	660	670	3	92
1035	1.773	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	660	670	3	93
1120	1.777	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	655	665	4	92
959	1.743	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	108	0.03	0.22	0.008	0.008	0.04	660	670	3	93
981	1.766	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	102	0.032	0.22	0.008	0.009	0.04	665	665	4	92
998	1.769	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	660	665	3	92
1110	1.761	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	109	0.033	0.23	0.008	0.009	0.04	665	665	4	93
957	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	670	3	92
994	1.75	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	106	0.032	0.21	0.009	0.009	0.04	660	670	3	93
989	1.746	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	655	665	4	92
976	1.746	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	660	665	3	92
956	1.751	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1010	1.763	200	0.33*851*3660	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1311	1.924	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1310	1.937	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1309	1.928	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1308	1.918	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1307	1.932	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	660	670	3	93
1306	1.925	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1305	1.921	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1304	1.915	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1303	1.92	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1302	1.918	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	660	670	3	93
1299	1.95	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1298	1.927	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1296	1.902	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1295	1.923	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	655	665	4	92



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1292	1.917	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	660	670	3	93
1290	1.903	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1287	1.919	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1286	1.924	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1289	1.931	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1291	1.915	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	660	670	3	93
1293	1.937	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1300	1.929	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	660	670	3	92
1301	1.917	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	660	670	3	93
1312	1.287	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	655	665	4	92
1288	1.932	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	660	670	3	93
1294	1.906	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	665	665	4	93
1297	1.924	200	0.33*851*4000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	660	670	3	92
	1135.541																	

NOTE: 1、 R_{el} : lower yield strength R_m : tensile strength A: percentage elongation after fracture
2、1 N/mm²=1 MPa

证明本表所列制品，均依材料规格制造及试验，并符合规格之要求
WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULT IN ACCORDANCE WITH
THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.



XINGHAN

冠县众冠新材料材有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD.

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

产品质量证明书

MILL'S TEST CERTIFICATE

订货单位 CUSTOMER		CUMIC STEEL LIMITED								钢号 GR.37	产品名称 PRODUCT					GALVALUME STEEL CORRUGATED SHEETS 5V			
收货单位 PURCHASER		CUMIC STEEL LIMITED									签发日期 DATE					2024.8.10			
标准 SPECIFICATION		ASTM A792M									合同号 CONTRACT NO.					ZG202405172977			
捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES				
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB	
364	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76	
363	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75	
369	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76	
371	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75	
372	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	455	465	27	76	
373	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.22	0.008	0.009	0.04	450	470	28	76	
374	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	455	465	26	76	
381	0.934	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.032	0.21	0.009	0.009	0.04	450	465	27	76	
382	0.934	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	465	26	75	
385	0.935	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	470	27	76	
386	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.03	0.22	0.008	0.008	0.04	455	470	26	75	
390	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	27	76	
392	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	465	26	76	
397	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	76	
398	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	27	75	
399	0.937	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	28	76	
401	0.934	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	27	76	
403	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	455	470	28	75	
405	0.935	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	450	465	27	75	
408	0.941	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	470	26	76	
409	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	465	27	75	
410	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76	
413	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.033	0.23	0.008	0.009	0.04	455	470	28	76	

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
414	0.943	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	455	465	27	75
415	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	28	76
416	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	455	470	27	76
417	0.945	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	470	28	75
418	0.941	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	450	465	27	75
419	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	455	470	26	76
420	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.03	0.22	0.008	0.008	0.04	450	465	27	75
421	0.941	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	470	27	76
422	0.941	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.032	0.22	0.008	0.009	0.04	455	470	28	76
423	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	75
424	0.941	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.21	0.009	0.009	0.04	455	465	26	76
435	0.934	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	450	465	27	76
436	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	455	470	28	76
437	0.941	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	465	27	75
438	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.22	0.008	0.009	0.04	455	470	26	76
439	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	75
440	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.21	0.009	0.009	0.04	455	465	26	76
441	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.031	0.25	0.007	0.01	0.04	455	465	27	76
442	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.035	0.26	0.008	0.009	0.04	450	470	28	76
443	0.932	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.03	0.22	0.008	0.008	0.04	455	470	26	76
444	0.937	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.032	0.22	0.008	0.009	0.04	450	465	27	75
447	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	465	28	76
448	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.033	0.23	0.008	0.009	0.04	450	465	27	76
449	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.21	0.009	0.009	0.04	455	465	26	75
450	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	450	470	27	76
453	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	26	75
454	0.943	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.035	0.26	0.008	0.009	0.04	455	465	27	76
459	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	450	470	28	76
460	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	465	28	76
365	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	450	465	27	76
366	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	465	26	75
461	0.932	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	450	470	27	76
458	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	470	26	75
457	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	76
456	0.937	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	450	470	28	76
455	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.035	0.26	0.008	0.009	0.04	455	465	27	75

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
452	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	470	28	76
451	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	455	470	27	76
446	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	470	28	75
445	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	450	465	27	75
434	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	455	470	26	76
433	0.935	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.03	0.22	0.008	0.008	0.04	450	465	27	75
432	0.944	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.22	0.008	0.009	0.04	455	470	27	76
431	0.945	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	470	28	76
430	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.033	0.23	0.008	0.009	0.04	450	465	27	75
429	0.937	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
428	0.945	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.21	0.009	0.009	0.04	450	465	27	76
427	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
426	0.941	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
425	0.944	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
412	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
411	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
407	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
406	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
404	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
402	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
400	0.937	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
396	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
395	0.937	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
394	0.937	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
393	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
391	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
389	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
388	0.943	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
387	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
384	0.942	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
383	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
380	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
379	0.935	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
378	0.932	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
377	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
376	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
375	0.936	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
370	0.938	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
368	0.939	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
367	0.94	200	0.33*895*2000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
214	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
215	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
223	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
236	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
237	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
251	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
258	1.178	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
276	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
278	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
282	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
290	1.155	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
309	1.162	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
322	1.175	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
268	1.182	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
275	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
220	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
225	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
232	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
234	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
238	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
239	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
249	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
252	1.174	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
254	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
255	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
256	1.178	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
257	1.178	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
265	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
266	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
267	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
269	1.176	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
270	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
277	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
279	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
288	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
293	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
294	1.174	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
295	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
297	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
299	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
300	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
302	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
304	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
306	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
308	1.161	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
310	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
313	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
314	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
317	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
318	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
319	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
320	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
321	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
324	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
327	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
199	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
201	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
204	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
211	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
212	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
221	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
224	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
226	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
227	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
228	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
229	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
230	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
231	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
233	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
242	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
246	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
247	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
248	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
250	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
259	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
260	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
261	1.176	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
262	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
264	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
281	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
284	1.162	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
285	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
286	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
289	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
291	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
292	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
296	1.161	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
298	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
301	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
303	1.174	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
307	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
311	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
312	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
315	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
323	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
203	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
205	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
206	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
208	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
209	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
213	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
217	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
218	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
219	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
222	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
235	1.175	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
240	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
243	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
244	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
245	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
263	1.176	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
271	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
272	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
273	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
274	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
280	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
283	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
287	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
305	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
316	1.16	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
333	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
334	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
336	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
337	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
342	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
343	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
359	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
360	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
361	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
362	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
358	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
357	1.173	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
356	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
355	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
354	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
353	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
352	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
351	1.168	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
350	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
349	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
348	1.17	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
347	1.162	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
346	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
345	1.161	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
344	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
341	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
340	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
339	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
338	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
335	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
332	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
331	1.162	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
330	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
329	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
328	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
326	1.164	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
325	1.166	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
253	1.175	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
241	1.172	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
216	1.169	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
210	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
207	1.163	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
202	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
200	1.167	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
198	1.171	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
462	1.161	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
463	1.165	200	0.33*895*2500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
117	1.412	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
121	1.409	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
123	1.4	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
125	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
127	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
128	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
140	1.394	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
142	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
145	1.402	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
146	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
148	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
156	1.404	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
157	1.4	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
158	1.402	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
159	1.408	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
160	1.417	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
161	1.408	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
163	1.407	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
171	1.403	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
173	1.406	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
176	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
178	1.406	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
181	1.407	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
184	1.398	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
185	1.39	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
186	1.4	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
187	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
188	1.398	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
190	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
191	1.393	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
192	1.405	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
193	1.403	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
197	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
177	1.401	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
179	1.406	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
180	1.41	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
196	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
111	1.393	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
113	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
115	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
116	1.407	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
118	1.409	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
119	1.411	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
120	1.417	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
122	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
124	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
126	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
129	1.398	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
131	1.394	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
132	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
135	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
136	1.393	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
137	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
155	1.401	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
162	1.409	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
164	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
165	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
166	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
167	1.403	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
168	1.401	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
169	1.405	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
170	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
172	1.403	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
174	1.412	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
175	1.412	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
182	1.406	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
183	1.407	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
189	1.398	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
194	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
195	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
108	1.394	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
109	1.4	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
110	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
112	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
114	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
130	1.397	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
133	1.394	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
134	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
138	1.394	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
139	1.393	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
141	1.393	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
143	1.389	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
144	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
147	1.398	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
149	1.395	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
150	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
151	1.407	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
152	1.408	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
153	1.396	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
154	1.399	200	0.33*895*3000	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
37	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
39	1.63	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
41	1.63	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
42	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
43	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
44	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
45	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
46	1.625	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
47	1.63	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
48	1.628	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
63	1.639	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
64	1.632	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
65	1.629	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
66	1.629	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
67	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
68	1.632	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
69	1.646	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
70	1.639	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
71	1.64	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
72	1.642	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
76	1.632	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
77	1.632	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
79	1.636	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
80	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
82	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
83	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
85	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
36	1.617	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
49	1.626	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
50	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
51	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
55	1.632	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
56	1.629	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
57	1.629	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
58	1.629	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
59	1.628	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
60	1.629	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
74	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
75	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
78	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
84	1.644	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
86	1.633	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
88	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
91	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
93	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
95	1.641	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
96	1.636	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
98	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
99	1.628	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
100	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
101	1.643	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
102	1.645	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
105	1.633	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
106	1.632	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
107	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
73	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
11	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
24	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
25	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
27	1.647	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
28	1.65	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
29	1.649	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
31	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
32	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
33	1.63	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
34	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	465	27	76
35	1.625	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
38	1.621	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
40	1.63	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75
52	1.626	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
53	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
54	1.639	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
61	1.634	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
62	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
81	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.031	0.25	0.007	0.01	0.04	455	470	28	76
87	1.634	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.035	0.26	0.008	0.009	0.04	450	465	27	75
89	1.648	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	470	26	76
90	1.641	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	75
92	1.628	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	455	465	27	75
94	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	28	76
97	1.629	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.033	0.23	0.008	0.009	0.04	455	470	27	76
103	1.634	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.21	0.009	0.009	0.04	455	470	28	75
104	1.631	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.031	0.25	0.007	0.01	0.04	450	465	27	75
1	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.035	0.26	0.008	0.009	0.04	455	470	26	76
2	1.639	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.03	0.22	0.008	0.008	0.04	450	465	27	75
3	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.032	0.22	0.008	0.009	0.04	455	470	27	76
4	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	455	470	28	76
5	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	450	465	27	75
6	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	26	76
7	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	450	465	27	76
8	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	470	28	76
9	1.641	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	465	27	75
10	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	26	76
12	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.033	0.23	0.008	0.009	0.04	450	465	27	75
13	1.637	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.21	0.009	0.009	0.04	455	465	26	76
14	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.031	0.25	0.007	0.01	0.04	455	470	27	76
15	1.64	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.035	0.26	0.008	0.009	0.04	450	470	28	76
16	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.03	0.22	0.008	0.008	0.04	455	470	26	76
17	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.032	0.22	0.008	0.009	0.04	450	465	27	75



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
18	1.634	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	28	76
19	1.627	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.033	0.23	0.008	0.009	0.04	450	465	27	76
20	1.63	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.032	0.21	0.009	0.009	0.04	455	465	26	75
21	1.628	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	450	470	27	76
22	1.632	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	26	75
23	1.636	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.035	0.26	0.008	0.009	0.04	455	465	27	76
26	1.645	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	102	0.032	0.22	0.008	0.009	0.04	450	470	28	76
30	1.643	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.033	0.23	0.008	0.009	0.04	455	465	26	76
464	1.626	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	109	0.032	0.21	0.009	0.009	0.04	450	465	27	76
465	1.636	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.031	0.25	0.007	0.01	0.04	455	465	26	75
466	1.628	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.035	0.26	0.008	0.009	0.04	450	470	27	76
467	1.654	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	105	0.03	0.22	0.008	0.008	0.04	455	470	26	75
468	1.635	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	107	0.032	0.22	0.008	0.009	0.04	455	465	27	76
469	1.621	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.22	0.008	0.009	0.04	455	465	26	76
470	1.651	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	103	0.033	0.23	0.008	0.009	0.04	450	465	27	76
471	1.643	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	104	0.032	0.21	0.009	0.009	0.04	455	465	27	75
472	1.638	200	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	106	0.031	0.25	0.007	0.01	0.04	455	470	28	76
473	1.055	126	0.33*895*3500	CHROMATED	72h	55	43.4	1.6	108	0.032	0.22	0.008	0.009	0.04	455	470	27	76
	604.686																	

NOTE: 1、ReL : lower yield strength Rm : tensile strength A: percentage elongation after fracture
2、1 N/mm2=1 MPa

证明本表所列制品，均依材料规格制造及试验，并符合规格之要求

WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULT IN ACCORDANCE WITH THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.



XINGHAN

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD.

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

产品质量证明书

MILL'S TEST CERTIFICATE

订货单位 CUSTOMER		CUMIC STEEL LIMITED								钢号	GR.37					产品名称 PRODUCT		GALVALUME STEEL CORRUGATED SHEETS	
收货单位 PURCHASER		CUMIC STEEL LIMITED									签发日期 OF ISSUE		DATE		2024.8.10				
标准 SPECIFICATION		ASTM A792M									合同号 NO.		CONTRACT		ZG202405172977				
捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES				
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB	
1252	1.738	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	155	0.03	0.22	0.008	0.008	0.04	665	665	4	92	
1256	1.726	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	158	0.032	0.22	0.008	0.009	0.04	660	665	3	92	
1257	1.731	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.22	0.008	0.009	0.04	665	665	4	93	
1259	1.733	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	156	0.033	0.23	0.008	0.009	0.04	660	670	3	92	
1264	1.733	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.21	0.009	0.009	0.04	660	670	3	93	
1250	1.722	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92	
1265	1.728	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92	
1260	1.73	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93	
1251	1.731	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92	
1254	1.731	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92	
1258	1.733	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92	
1267	1.736	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92	
1255	1.737	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93	
1263	1.739	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92	
1262	1.742	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92	
1266	1.744	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92	
1261	1.745	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92	
1268	1.74	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93	
1253	1.731	200	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92	
1269	2.211	255	0.4*851*3000	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92	
1281	2.073	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92	
1285	2.053	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92	
1272	2.097	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93	

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%)			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1274	2.116	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1277	2.106	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1279	2.099	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1280	2.106	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1282	2.105	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1283	2.087	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1270	2.117	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1273	2.096	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1275	2.102	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1276	2.062	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1321	2.097	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1278	2.104	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1314	2.104	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1325	2.104	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1338	2.106	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1313	2.107	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1317	2.111	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1327	2.12	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1284	2.127	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1271	2.119	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1318	2.122	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1319	2.134	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1320	2.119	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1322	2.104	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1323	2.1	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1324	2.111	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1333	2.129	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1334	2.111	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1337	2.11	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1339	2.109	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1419	2.106	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1315	2.108	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1328	2.106	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1331	2.119	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1417	2.103	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1420	2.117	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
1421	2.107	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1424	1.888	178	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1423	2.104	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1422	2.113	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1418	2.104	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1416	2.11	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1336	2.102	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1335	2.11	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
1332	2.12	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	665	665	4	93
1330	2.106	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	660	670	3	92
1329	2.102	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	660	665	3	92
1326	2.102	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	655	665	4	92
1316	2.116	200	0.4*851*3660	CHROMATED	72h	55	43.4	1.6	153	0.031	0.25	0.007	0.01	0.04	660	665	3	92
	144.471																	

NOTE: 1、 ReL : lower yield strength Rm : tensile strength A: percentage elongation after fracture
2、 1 N/mm2=1 MPa

证明本表所列制品，均依材料规格制造及试验，并符合规格之要求

WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULT IN ACCORDANCE WITH THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.

质量部
DEPARTM



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977								
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10								
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATING	涂层性能 COAT PROPERTY							
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R_{eL}	R_m	A	硬度 HARDNESS	两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss	涂层色差 chromaticity difference
						%	%	%	%	%	Mpa			%	g/m ²								
1426	1.387	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	432	490	25	78	53	20	8	2T	2T	9J	120/80	57.8	0.31
1427	1.412	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	54	20	8	2T	2T	9J	120/80	58.6	0.31
1431	1.392	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	56	20	8	2T	2T	9J	120/80	58.5	0.31
1432	1.395	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	54	20	8	2T	2T	9J	120/80	59.6	0.33
1434	1.384	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	79	55	20	8	2T	2T	9J	120/80	57.8	0.31
1435	1.385	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	58	20	8	2T	2T	9J	120/80	57.8	0.31
1436	1.401	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	495	25	80	59	20	8	2T	2T	9J	120/80	58.6	0.31
1437	1.392	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	57	20	8	2T	2T	9J	120/80	58.5	0.32
1438	1.388	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	57	20	8	2T	2T	9J	120/80	59.6	0.31
1439	1.386	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	78	54	20	8	2T	2T	9J	120/80	57.8	0.31
1441	1.384	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	56	20	8	2T	2T	9J	120/80	57.8	0.31
1442	1.38	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.32
1446	1.402	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	55	20	8	2T	2T	9J	120/80	58.5	0.31
1447	1.409	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	54	20	8	2T	2T	9J	120/80	59.6	0.33
1452	1.385	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	55	20	8	2T	2T	9J	120/80	57.8	0.31
1454	1.383	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	58	20	8	2T	2T	9J	120/80	57.8	0.31
1455	1.396	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	59	20	8	2T	2T	9J	120/80	58.6	0.31
1457	1.387	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	79	57	20	8	2T	2T	9J	120/80	58.5	0.32
1459	1.39	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	78	57	20	8	2T	2T	9J	120/80	59.6	0.31



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977								
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10								
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY							
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{el}	R _m	A	硬度 HARD NESS		两面 BOTH g/m ²	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss
1461	1.392	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	79	54	20	8	2T	2T	9J	120/80	57.8	0.31
1575	1.395	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	56	20	8	2T	2T	9J	120/80	57.8	0.31
1577	1.384	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	495	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.32
1579	1.393	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	55	20	8	2T	2T	9J	120/80	58.5	0.31
1581	1.399	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	54	20	8	2T	2T	9J	120/80	59.6	0.33
1585	1.386	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	55	20	8	2T	2T	9J	120/80	57.8	0.31
1588	1.385	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	58	20	8	2T	2T	9J	120/80	57.8	0.31
1591	1.402	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	59	20	8	2T	2T	9J	120/80	58.6	0.31
1594	1.389	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	78	57	20	8	2T	2T	9J	120/80	58.5	0.32
1595	1.384	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	57	20	8	2T	2T	9J	120/80	59.6	0.31
1596	1.388	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	54	20	8	2T	2T	9J	120/80	57.8	0.31
1597	1.389	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	57.8	0.31
1599	1.381	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	54	20	8	2T	2T	9J	120/80	58.6	0.32
1600	1.306	188	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	55	20	8	2T	2T	9J	120/80	58.5	0.31
1578	1.377	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	54	20	8	2T	2T	9J	120/80	59.6	0.33
1430	1.38	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	79	55	20	8	2T	2T	9J	120/80	57.8	0.31
1460	1.381	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	58	20	8	2T	2T	9J	120/80	57.8	0.31
1580	1.382	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	495	25	80	59	20	8	2T	2T	9J	120/80	58.6	0.31
1583	1.382	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	57	20	8	2T	2T	9J	120/80	58.5	0.32



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{el}	R _m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss	涂层色差 chromatici ty difference	
1451	1.384	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	57	20	8	2T	2T	9J	120/80	59.6	0.31		
1592	1.384	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	78	54	20	8	2T	2T	9J	120/80	57.8	0.31		
1448	1.385	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	56	20	8	2T	2T	9J	120/80	57.8	0.31		
1445	1.386	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.32		
1453	1.386	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	55	20	8	2T	2T	9J	120/80	58.5	0.31		
1456	1.386	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	54	20	8	2T	2T	9J	120/80	59.6	0.33		
1576	1.386	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	55	20	8	2T	2T	9J	120/80	57.8	0.31		
1450	1.387	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	58	20	8	2T	2T	9J	120/80	57.8	0.31		
1582	1.387	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	59	20	8	2T	2T	9J	120/80	58.6	0.31		
1458	1.388	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	79	57	20	8	2T	2T	9J	120/80	58.5	0.32		
1589	1.389	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	78	57	20	8	2T	2T	9J	120/80	59.6	0.31		
1428	1.39	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	79	54	20	8	2T	2T	9J	120/80	57.8	0.31		
1440	1.391	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	56	20	8	2T	2T	9J	120/80	57.8	0.31		
1590	1.391	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	495	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.32		
1429	1.393	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	55	20	8	2T	2T	9J	120/80	58.5	0.31		
1574	1.394	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	54	20	8	2T	2T	9J	120/80	59.6	0.33		
1587	1.394	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	55	20	8	2T	2T	9J	120/80	57.8	0.31		
1425	1.395	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	58	20	8	2T	2T	9J	120/80	57.8	0.31		
1443	1.396	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	59	20	8	2T	2T	9J	120/80	58.6	0.31		



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977								
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10								
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY							
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{eL}	R _m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss
1433	1.398	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	78	57	20	8	2T	2T	9J	120/80	58.5	0.32
1586	1.399	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	57	20	8	2T	2T	9J	120/80	59.6	0.31
1593	1.4	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	54	20	8	2T	2T	9J	120/80	57.8	0.31
1598	1.4	200	0.33*851*3000	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	57.8	0.31
1642	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	54	20	8	2T	2T	9J	120/80	58.6	0.32
1601	1.689	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	55	20	8	2T	2T	9J	120/80	58.5	0.31
1606	1.689	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	54	20	8	2T	2T	9J	120/80	59.6	0.33
1613	1.689	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	79	55	20	8	2T	2T	9J	120/80	57.8	0.31
1630	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	58	20	8	2T	2T	9J	120/80	57.8	0.31
1615	1.694	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	495	25	80	59	20	8	2T	2T	9J	120/80	58.6	0.31
1567	1.696	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	57	20	8	2T	2T	9J	120/80	58.5	0.32
1699	1.696	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	57	20	8	2T	2T	9J	120/80	59.6	0.31
1561	1.702	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	78	54	20	8	2T	2T	9J	120/80	57.8	0.31
1703	1.702	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	56	20	8	2T	2T	9J	120/80	57.8	0.31
1713	1.703	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.32
1565	1.695	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	55	20	8	2T	2T	9J	120/80	58.5	0.31
1710	1.695	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	54	20	8	2T	2T	9J	120/80	59.6	0.33
1693	1.708	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	55	20	8	2T	2T	9J	120/80	57.8	0.31
1569	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	58	20	8	2T	2T	9J	120/80	57.8	0.31



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{el}	R _m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss	涂层色差 chromatici ty difference	
																									%
1653	1.691	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	59	20	8	2T	2T	9J	120/80	58.6	0.31		
1657	1.693	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	79	57	20	8	2T	2T	9J	120/80	58.5	0.32		
1676	1.694	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	78	57	20	8	2T	2T	9J	120/80	59.6	0.31		
1603	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	79	54	20	8	2T	2T	9J	120/80	57.8	0.31		
1640	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	56	20	8	2T	2T	9J	120/80	57.8	0.31		
1660	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	495	25	80	55	20	8	2T	2T	9J	120/80	58.6	0.31		
1661	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	58	20	8	2T	2T	9J	120/80	58.5	0.31		
1658	1.655	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	59	20	8	2T	2T	9J	120/80	59.6	0.31		
1608	1.676	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	78	57	20	8	2T	2T	9J	120/80	57.8	0.32		
1654	1.683	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	57	20	8	2T	2T	9J	120/80	57.8	0.31		
1558	1.683	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.31		
1560	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	58.5	0.31		
1562	1.7	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	54	20	8	2T	2T	9J	120/80	59.6	0.31		
1637	1.689	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	55	20	8	2T	2T	9J	120/80	57.8	0.31		
1584	1.392	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	54	20	8	2T	2T	9J	120/80	57.8	0.33		
1622	1.666	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	55	20	8	2T	2T	9J	120/80	58.6	0.31		
1624	1.678	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	58	20	8	2T	2T	9J	120/80	58.5	0.31		
1684	1.688	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	59	20	8	2T	2T	9J	120/80	59.6	0.31		
1636	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	79	57	20	8	2T	2T	9J	120/80	57.8	0.32		



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{el}	R _m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦 拭 wipe coating	光泽 gloss	涂层色 差 chromatici ty difference	
																									%
1641	1.681	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	57	20	8	2T	2T	9J	120/80	57.8	0.31		
1644	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	495	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.31		
1645	1.681	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	56	20	8	2T	2T	9J	120/80	58.5	0.31		
1656	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	55	20	8	2T	2T	9J	120/80	59.6	0.31		
1444	1.385	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	58	20	8	2T	2T	9J	120/80	57.8	0.31		
1449	1.387	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	59	20	8	2T	2T	9J	120/80	57.8	0.31		
1678	1.688	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	80	57	20	8	2T	2T	9J	120/80	58.6	0.32		
1673	1.703	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	78	57	20	8	2T	2T	9J	120/80	58.5	0.31		
1672	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	77	54	20	8	2T	2T	9J	120/80	59.6	0.31		
1714	1.623	192	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	56	20	8	2T	2T	9J	120/80	57.8	0.31		
1618	1.678	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	54	20	8	2T	2T	9J	120/80	57.8	0.32		
1651	1.682	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	55	20	8	2T	2T	9J	120/80	58.6	0.31		
1650	1.684	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	54	20	8	2T	2T	9J	120/80	58.5	0.33		
1638	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	55	20	8	2T	2T	9J	120/80	59.6	0.31		
1643	1.686	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	79	58	20	8	2T	2T	9J	120/80	57.8	0.31		
1674	1.688	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	59	20	8	2T	2T	9J	120/80	57.8	0.31		
1647	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	495	25	80	57	20	8	2T	2T	9J	120/80	58.6	0.32		
1691	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	57	20	8	2T	2T	9J	120/80	58.5	0.31		
1679	1.695	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	54	20	8	2T	2T	9J	120/80	59.6	0.31		



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{eL}	R _m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss	涂层色差 chromatici ty difference	
						%	%	%	%	%	Mpa		%												g/m ²
1677	1.696	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	57.8	0.31		
1602	1.698	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	55	20	8	2T	2T	9J	120/80	57.8	0.31		
1563	1.699	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	58	20	8	2T	2T	9J	120/80	58.6	0.31		
1701	1.704	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	59	20	8	2T	2T	9J	120/80	58.5	0.31		
1566	1.721	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	57	20	8	2T	2T	9J	120/80	59.6	0.32		
1705	1.683	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	57	20	8	2T	2T	9J	120/80	57.8	0.31		
1680	1.689	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	78	54	20	8	2T	2T	9J	120/80	57.8	0.31		
1706	1.681	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	56	20	8	2T	2T	9J	120/80	58.6	0.31		
1697	1.682	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	54	20	8	2T	2T	9J	120/80	58.5	0.32		
1570	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	55	20	8	2T	2T	9J	120/80	59.6	0.31		
1623	1.686	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	79	54	20	8	2T	2T	9J	120/80	57.8	0.33		
1639	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	55	20	8	2T	2T	9J	120/80	57.8	0.31		
1707	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	495	25	80	58	20	8	2T	2T	9J	120/80	58.6	0.31		
1708	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	59	20	8	2T	2T	9J	120/80	58.5	0.31		
1698	1.691	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	79	57	20	8	2T	2T	9J	120/80	59.6	0.32		
1675	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	78	57	20	8	2T	2T	9J	120/80	57.8	0.31		
1692	1.694	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	77	54	20	8	2T	2T	9J	120/80	57.8	0.31		
1616	1.704	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	56	20	8	2T	2T	9J	120/80	58.6	0.31		
1702	1.711	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	55	20	8	2T	2T	9J	120/80	58.5	0.31		



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977								
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10								
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY							
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{eL}	R _m	A	硬度 HARDNESS	两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦 拭 wipe coating	光泽 gloss	涂层色 差 chromatic ity difference
1626	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	58	20	8	2T	2T	9J	120/80	59.6	0.31
1557	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	59	20	8	2T	2T	9J	120/80	57.8	0.31
1556	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	78	57	20	8	2T	2T	9J	120/80	57.8	0.32
1568	1.691	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	57	20	8	2T	2T	9J	120/80	58.6	0.31
1649	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	54	20	8	2T	2T	9J	120/80	58.5	0.31
1682	1.707	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	59.6	0.31
1664	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	79	54	20	8	2T	2T	9J	120/80	57.8	0.32
1666	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	55	20	8	2T	2T	9J	120/80	57.8	0.31
1670	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	495	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.33
1668	1.693	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	55	20	8	2T	2T	9J	120/80	58.5	0.31
1669	1.693	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	58	20	8	2T	2T	9J	120/80	59.6	0.31
1625	1.691	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	59	20	8	2T	2T	9J	120/80	57.8	0.31
1609	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	57	20	8	2T	2T	9J	120/80	57.8	0.32
1627	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	80	57	20	8	2T	2T	9J	120/80	58.5	0.31
1683	1.688	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	78	54	20	8	2T	2T	9J	120/80	58.5	0.31
1685	1.681	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	56	20	8	2T	2T	9J	120/80	59.6	0.31
1648	1.683	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	55	20	8	2T	2T	9J	120/80	57.8	0.31(2)
1667	1.684	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	58	20	8	2T	2T	9J	120/80	57.8	0.31
1604	1.686	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	59	20	8	2T	2T	9J	120/80	58.6	0.31



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977								
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10								
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY							
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{el}	R _m	A	硬度 HARD	两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦 拭 wipe coating	光泽 gloss	涂层色 差 chromatici ty difference
						%	%	%	%	%	Mpa	%	g/m ²										
1681	1.686	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	79	57	20	8	2T	2T	9J	120/80	58.5	0.32
1652	1.686	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	78	57	20	8	2T	2T	9J	120/80	59.6	0.31
1663	1.686	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	79	54	20	8	2T	2T	9J	120/80	57.8	0.31
1655	1.682	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	56	20	8	2T	2T	9J	120/80	57.8	0.31
1665	1.684	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	495	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.32
1646	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	55	20	8	2T	2T	9J	120/80	58.5	0.31
1634	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	54	20	8	2T	2T	9J	120/80	59.6	0.33
1659	1.687	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	55	20	8	2T	2T	9J	120/80	57.8	0.31
1709	1.688	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	58	20	8	2T	2T	9J	120/80	57.8	0.31
1686	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	59	20	8	2T	2T	9J	120/80	58.6	0.31
1690	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	78	57	20	8	2T	2T	9J	120/80	58.5	0.32
1700	1.691	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	57	20	8	2T	2T	9J	120/80	59.6	0.31
1712	1.692	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	54	20	8	2T	2T	9J	120/80	57.8	0.31
1620	1.693	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	57.8	0.31
1687	1.693	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	55	20	8	2T	2T	9J	120/80	58.6	0.31
1711	1.693	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	58	20	8	2T	2T	9J	120/80	58.5	0.31
1694	1.695	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	59	20	8	2T	2T	9J	120/80	59.6	0.31
1628	1.696	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	79	57	20	8	2T	2T	9J	120/80	57.8	0.32
1704	1.696	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	57	20	8	2T	2T	9J	120/80	57.8	0.31



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO.,LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R_{el}	R_m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss	涂层色差 chromatici ty difference	
1619	1.697	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	495	25	80	54	20	8	2T	2T	9J	120/80	58.6	0.31		
1662	1.699	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	56	20	8	2T	2T	9J	120/80	58.5	0.31		
1671	1.699	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	54	20	8	2T	2T	9J	120/80	59.6	0.32		
1695	1.701	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	55	20	8	2T	2T	9J	120/80	57.8	0.31		
1632	1.66	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	54	20	8	2T	2T	9J	120/80	57.8	0.33		
1612	1.675	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	80	55	20	8	2T	2T	9J	120/80	58.6	0.31		
1629	1.681	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	58	20	8	2T	2T	9J	120/80	58.5	0.31		
1631	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	59	20	8	2T	2T	9J	120/80	59.6	0.31		
1633	1.686	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	79	57	20	8	2T	2T	9J	120/80	57.8	0.32		
1635	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	78	57	20	8	2T	2T	9J	120/80	57.8	0.31		
1559	1.691	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	77	54	20	8	2T	2T	9J	120/80	58.6	0.31		
1611	1.696	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	56	20	8	2T	2T	9J	120/80	58.5	0.31		
1571	1.697	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	55	20	8	2T	2T	9J	120/80	59.6	0.31		
1621	1.697	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	79	58	20	8	2T	2T	9J	120/80	57.8	0.31		
1689	1.697	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	59	20	8	2T	2T	9J	120/80	57.8	0.31		
1688	1.703	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	495	25	80	57	20	8	2T	2T	9J	120/80	58.6	0.31		
1696	1.707	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	57	20	8	2T	2T	9J	120/80	58.5	0.31		
1614	1.712	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	54	20	8	2T	2T	9J	120/80	59.6	0.31		
1605	1.722	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	57.8	0.31		



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书


冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R_{el}	R_m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦 拭 wipe coating	光泽 gloss	涂层色 差 chromatici ty difference	
1617	1.729	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	54	20	8	2T	2T	9J	120/80	58.5	0.32		
1607	1.685	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	55	20	8	2T	2T	9J	120/80	59.6	0.31		
1610	1.69	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	54	20	8	2T	2T	9J	120/80	57.8	0.33		
1555	1.695	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	55	20	8	2T	2T	9J	120/80	58.5	0.31		
1564	1.695	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	58	20	8	2T	2T	9J	120/80	59.6	0.31		
1572	1.697	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	59	20	8	2T	2T	9J	120/80	57.8	0.31		
1573	1.698	200	0.33*851*3660	RAL9017	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	57	20	8	2T	2T	9J	120/80	57.8	0.32		
1532	1.695	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	57	20	8	2T	2T	9J	120/80	28.6	0.31		
1535	1.69	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	78	54	20	8	2T	2T	9J	120/80	28.5	0.31		
1542	1.699	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	79	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1531	1.742	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1553	1.686	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	495	25	80	54	20	8	2T	2T	9J	120/80	29.7	0.32		
1551	1.69	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	55	20	8	2T	2T	9J	120/80	28.5	0.31		
1716	1.536	181	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	54	20	8	2T	2T	9J	120/80	29.6	0.33		
1715	1.709	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	55	20	8	2T	2T	9J	120/80	29.7	0.31		
1552	1.691	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	58	20	8	2T	2T	9J	120/80	28.6	0.31		
1543	1.687	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	59	20	8	2T	2T	9J	120/80	29.1	0.31		
1522	1.693	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	57	20	8	2T	2T	9J	120/80	27.8	0.32		
1545	1.696	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	485	26	77	57	20	8	2T	2T	9J	120/80	28.6	0.31		



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO.,LTD

地址: 中国山东聊城冠县新世纪工业园

Address:Guan Xian industry Park,Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024.8.10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R _{el}	R _m	A	硬度 HARD NESS		两面 BOTH g/m ²	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦 拭 wipe coating	光泽 gloss	涂层色 差 chromatici ty difference	
1547	1.698	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	54	20	8	2T	2T	9J	120/80	28.5	0.31		
1537	1.741	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1533	1.689	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	435	485	26	77	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1529	1.692	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	430	490	25	79	54	20	8	2T	2T	9J	120/80	29.7	0.32		
1546	1.692	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	78	55	20	8	2T	2T	9J	120/80	28.5	0.31		
1548	1.693	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	79	54	20	8	2T	2T	9J	120/80	29.6	0.33		
1526	1.695	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	55	20	8	2T	2T	9J	120/80	29.7	0.31		
1554	1.695	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	495	25	80	58	20	8	2T	2T	9J	120/80	28.5	0.31		
1527	1.696	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	425	485	26	77	59	20	8	2T	2T	9J	120/80	29.1	0.31		
1541	1.696	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	57	20	8	2T	2T	9J	120/80	27.8	0.32		
1544	1.697	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	57	20	8	2T	2T	9J	120/80	28.6	0.31		
1550	1.698	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	54	20	8	2T	2T	9J	120/80	28.5	0.31		
1525	1.7	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	80	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1549	1.703	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	78	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1540	1.709	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	54	20	8	2T	2T	9J	120/80	29.7	0.32		
1536	1.712	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	79	55	20	8	2T	2T	9J	120/80	28.5	0.31		
1538	1.729	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	435	490	25	78	54	20	8	2T	2T	9J	120/80	29.6	0.31		
1539	1.746	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	430	485	26	77	55	20	8	2T	2T	9J	120/80	29.7	0.31		
1520	1.689	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	425	490	25	79	58	20	8	2T	2T	9J	120/80	28.5	0.31		



XINGHAN

MILL'S TEST CERTIFICATE
产品质量证明书

冠县众冠新材料有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD

地址: 中国山东聊城冠县新世纪工业园

Address: Guan Xian industry Park, Liaocheng, Shandong, China

定货单位 CUSTOMER			CUMIC STEEL LIMITED								合同号 CONTRACT NO.				ZG202405172977										
产品名称 NAME OF PRODUCT			PREPAINTED GALVALUME STEEL CORRUGATED SHEETS								证明书日期 T/C ISSUE DATE				2024. 8. 10										
捆号 PACK NO.	捆重 NET WEIGHT	片数 PIECE	规格及数量 MATERIAL DESCRIPTION			化学成分 CHEMICAL COMPOSITION% (熔炼分析 HEAT ANALYSIS)					力学性能 MECHANIC PROPERTIES				镀层重量 COATIN	涂层性能 COAT PROPERTY									
			规格mm SIZE	面漆 Top paint	背漆 Back paint	C	Mn	P	S	Si	R_{el}	R_m	A	硬度 HARDNESS		两面 BOTH	面漆涂 层厚度 facial coating	背漆涂 层厚度 Back coating	面漆涂 层T弯 T-bend	背漆涂 层T弯 T-bend	反向冲 击 impact test	涂层擦拭 wipe coating	光泽 gloss	涂层色差 chromaticity difference	
1519	1.695	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	59	20	8	2T	2T	9J	120/80	29.1	0.31		
1523	1.696	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	57	20	8	2T	2T	9J	120/80	27.8	0.32		
1524	1.696	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	57	20	8	2T	2T	9J	120/80	28.6	0.31		
1528	1.7	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	490	25	78	54	20	8	2T	2T	9J	120/80	28.5	0.31		
1534	1.7	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	79	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1521	1.705	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	56	20	8	2T	2T	9J	120/80	29.6	0.31		
1530	1.709	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	495	25	80	54	20	8	2T	2T	9J	120/80	29.7	0.32		
1517	1.696	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	455	485	26	77	55	20	8	2T	2T	9J	120/80	28.5	0.31		
1518	1.73	200	0.33*851*3660	RAL3009	RAL9002	0.035	0.26	0.008	0.009	0.04	450	490	25	79	55	20	8	2T	2T	9J	120/80	28.5	0.31		
	381.61																								

NOTE: R_{el} : lower yield strength R_m : tensile strength A: percentage elongation after fracture

证明本表所列制品, 均依材料规格制造及试验, 并符合规格之要求

WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULT IN ACCORDANCE WITH THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.



XINGHAN

冠县众冠新材料材有限公司

GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD.

地址：中国山东聊城冠县新世纪工业园

Address:Guan Xian industry Park,Liaocheng,Shandong,China

产品质量证明书

MILL'S TEST CERTIFICATE

订货单位 CUSTOMER		CUMIC STEEL LIMITED								钢号	GR.37					产品名称	PRODUCT			
收货单位 PURCHASER		CUMIC STEEL LIMITED									CHEMICAL COMPOSITION(%)					签发日期 OF ISSUE	DATE			
标准 SPECIFICATION		ASTM A792M									力学性能 MECHANIC PROPERTIES					合同号 NO.	CONTRACT			
捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	C	Mn	P	S	Si	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB		
						Al	Zn	Si												
1462	1.591	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63		
1467	1.583	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64		
1469	1.585	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5		
1470	1.583	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62		
1473	1.588	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63		
1474	1.579	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64		
1475	1.577	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5		
1476	1.582	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63		
1477	1.579	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64		
1478	1.582	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5		
1463	1.592	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62		
1464	1.584	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63		
1465	1.59	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64		
1482	1.58	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5		
1485	1.58	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63		
1491	1.587	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64		
1495	1.594	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5		
1496	1.589	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62		
1500	1.589	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63		
1503	1.582	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64		
1508	1.585	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5		
1511	1.587	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63		
1471	1.581	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64		
1472	1.584	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5		
1486	1.583	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62		



捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{el} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1489	1.585	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63
1493	1.582	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64
1494	1.587	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5
1501	1.578	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1502	1.588	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64
1504	1.579	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5
1510	1.584	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62
1492	1.581	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63
1509	1.584	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64
1468	1.585	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5
1505	1.576	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1479	1.58	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64
1515	1.58	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5
1497	1.583	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62
1513	1.587	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63
1466	1.59	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64
1490	1.592	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5
1506	1.597	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1507	1.6	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64
1487	1.581	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5
1480	1.578	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62
1481	1.581	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63
1488	1.582	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64
1514	1.582	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5
1512	1.585	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1499	1.587	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	31	64
1516	1.768	224	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.035	0.26	0.008	0.009	0.04	325	385	31	62.5
1483	1.583	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.03	0.22	0.008	0.008	0.04	330	388	32	62
1484	1.59	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.22	0.008	0.009	0.04	330	380	30	63
1498	1.586	200	0.35*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	333	385	32	64
1340	1.803	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.033	0.23	0.008	0.009	0.04	325	385	31	62.5
1341	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1349	1.802	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1356	1.808	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	32	64
1365	1.819	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.035	0.26	0.008	0.009	0.04	330	380	30	63
1380	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.032	0.22	0.008	0.009	0.04	333	385	31	64
1383	1.809	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.22	0.008	0.009	0.04	325	380	31	62.5
1396	1.809	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.033	0.23	0.008	0.009	0.04	330	385	32	62

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R_{eL} (N/mm ²)	R_m (N/mm ²)	A (%)	HRB
1397	1.806	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.21	0.009	0.009	0.04	330	385	31	63
1398	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.031	0.25	0.007	0.01	0.04	333	388	32	64
1399	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.035	0.26	0.008	0.009	0.04	325	380	31	62.5
1401	1.816	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.03	0.22	0.008	0.008	0.04	330	385	32	62
1402	1.815	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	330	385	30	63
1405	1.811	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.035	0.26	0.008	0.009	0.04	333	380	32	64
1407	1.814	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	325	380	31	62.5
1411	1.819	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	330	385	32	62
1412	1.816	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1413	1.825	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.031	0.25	0.007	0.01	0.04	333	385	32	64
1342	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.035	0.26	0.008	0.009	0.04	333	388	32	64
1344	1.811	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.03	0.22	0.008	0.008	0.04	325	380	31	62.5
1345	1.819	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.032	0.22	0.008	0.009	0.04	330	385	32	62
1347	1.817	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.22	0.008	0.009	0.04	330	385	30	63
1348	1.814	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.033	0.23	0.008	0.009	0.04	333	380	32	64
1352	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.032	0.21	0.009	0.009	0.04	325	380	31	62.5
1353	1.809	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	385	32	62
1354	1.818	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	330	380	30	63
1355	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.21	0.009	0.009	0.04	330	380	32	62
1357	1.811	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1358	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	32	64
1359	1.825	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.035	0.26	0.008	0.009	0.04	330	380	30	63
1363	1.815	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.032	0.22	0.008	0.009	0.04	333	385	31	64
1364	1.827	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.22	0.008	0.009	0.04	325	380	31	62.5
1367	1.807	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.033	0.23	0.008	0.009	0.04	330	385	32	62
1368	1.806	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.21	0.009	0.009	0.04	330	385	31	63
1369	1.808	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.031	0.25	0.007	0.01	0.04	333	388	32	64
1374	1.817	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.035	0.26	0.008	0.009	0.04	325	380	31	62.5
1376	1.822	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.03	0.22	0.008	0.008	0.04	330	385	32	62
1377	1.818	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	330	385	30	63
1387	1.815	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.035	0.26	0.008	0.009	0.04	333	380	32	64
1390	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	325	380	31	62.5
1392	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	330	385	32	62
1393	1.814	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1394	1.816	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.031	0.25	0.007	0.01	0.04	333	385	32	64
1395	1.802	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.035	0.26	0.008	0.009	0.04	333	388	32	64
1343	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.03	0.22	0.008	0.008	0.04	325	380	31	62.5
1351	1.808	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.032	0.22	0.008	0.009	0.04	330	385	32	62

捆号 PACK No.	重量 WEIGHT	片数 PIECE	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating			镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn	Si		C	Mn	P	S	Si	R _{eL} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
1361	1.817	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.22	0.008	0.009	0.04	330	385	30	63
1366	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.033	0.23	0.008	0.009	0.04	333	380	32	64
1372	1.822	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.032	0.21	0.009	0.009	0.04	325	380	31	62.5
1375	1.821	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	385	32	62
1381	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	330	380	30	63
1386	1.805	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.21	0.009	0.009	0.04	330	380	32	62
1400	1.815	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1403	1.815	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	333	385	32	64
1406	1.813	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.035	0.26	0.008	0.009	0.04	330	380	30	63
1409	1.815	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.032	0.22	0.008	0.009	0.04	333	385	31	64
1410	1.783	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.22	0.008	0.009	0.04	325	380	31	62.5
1414	1.82	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.033	0.23	0.008	0.009	0.04	330	385	32	62
1415	1.369	149	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.032	0.21	0.009	0.009	0.04	330	385	31	63
1360	1.811	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.031	0.25	0.007	0.01	0.04	333	388	32	64
1362	1.811	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.035	0.26	0.008	0.009	0.04	325	380	31	62.5
1370	1.82	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.03	0.22	0.008	0.008	0.04	330	385	32	62
1389	1.812	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.032	0.22	0.008	0.009	0.04	330	385	30	63
1350	1.806	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.035	0.26	0.008	0.009	0.04	333	380	32	64
1385	1.809	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.22	0.008	0.009	0.04	325	380	31	62.5
1346	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.033	0.23	0.008	0.009	0.04	330	385	32	62
1382	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.21	0.009	0.009	0.04	330	380	30	63
1408	1.811	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.031	0.25	0.007	0.01	0.04	333	385	32	64
1404	1.817	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	157	0.035	0.26	0.008	0.009	0.04	333	388	32	64
1371	1.818	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.03	0.22	0.008	0.008	0.04	325	380	31	62.5
1373	1.824	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	153	0.032	0.22	0.008	0.009	0.04	330	385	32	62
1388	1.812	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	154	0.032	0.22	0.008	0.009	0.04	330	385	30	63
1378	1.818	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	156	0.033	0.23	0.008	0.009	0.04	333	380	32	64
1379	1.82	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.032	0.21	0.009	0.009	0.04	325	380	31	62.5
1384	1.802	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	155	0.032	0.21	0.009	0.009	0.04	330	385	32	62
1391	1.81	200	0.4*1000*3000	CHROMATED	72h	55	43.4	1.6	158	0.031	0.25	0.007	0.01	0.04	330	380	30	63
	224.675																	

NOTE: 1、 ReL : lower yield strength Rm : tensile strength A: percentage elongation after fracture
2、 1 N/mm²=1 MPa

证明本表所列制品，均依材料规格制造及试验，并符合规格之要求
WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULT IN ACCORDANCE WITH
THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.



质量部
DEPARTM