



敬业 (营口) 中板有限公司
JINGYE (YINGKOU) MEDIUM PLATE CO.LTD.

辽宁省营口市老边区冶金街/115005

Yejinstreet, Laobiandistrict, Yingkou, Liaoning, P.R.China/115005

TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书

INSPECTION CERTIFICATE



订货单位 PURCHASER	CUMIC STEEL USA, INC	产品名称 PRODUCT	船用钢板 Hull Steel plate		
收货单位 CONSIGNEE	CUMIC STEEL USA, INC	合同编号 CONTRACT NO.	YGCAZANN251183005-01		
技术标准/牌号 SPEC/GRADE	LR RULES;LRB	交货状态 DELIVERY CONDITION	正火轧制(NR)	签发日期 DATE OF ISSUE	20260123
		证明书编号 CERTIFICATE NO.	260121Z00656	控制号 CONTROL NUMBER	DLN2600107
车号 TRAIN NO.		船号 HULL NO.		是否保性能 GUARANTEE OR NOT	是 YES

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	分段号 SECTION NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	化学成分 CHEMICAL ANALYSIS %														B 0A01 屈 服 强 度 MPa ReH	B 0A02 抗 拉 强 度 MPa Rm	B 0A03 断 后 伸 长 率 %	A 0C01 冲 击 单 值 J	A 0C02 冲 击 单 值 J	A 0C03 冲 击 单 值 J	A 0C02 冲 击 均 值 Ave
							C	Si	Mn	P	S	Als	Ti	Nb	Ni	Cr	Cu	Mo	CeqA								
							$\times 10^{-3}$	$\times 10^{-2}$	$\times 10^{-3}$	$\times 10^{-3}$	$\times 10^{-3}$	$\times 10^{-3}$	$\times 10^{-4}$	$\times 10^{-4}$	$\times 10^{-4}$	$\times 10^{-3}$	$\times 10^{-3}$	$\times 10^{-4}$	$\times 10^{-3}$								
26300497A	S61150215	S6115302101		8x2440x12000	1	1,839	141	25	806	18	3	28	200	30	330	71	29	70	275	322	450	34.5	83	90	79	84	
26300497A	S61150215	S6115302201		8x2440x12000	1	1,839	141	25	806	18	3	28	200	30	330	71	29	70	275	322	450	34.5	83	90	79	84	
26300497A	S61150215	S6115302301		8x2440x12000	1	1,839	141	25	806	18	3	28	200	30	330	71	29	70	275	322	450	34.5	83	90	79	84	
26300497A	S61150215	S6115303101		8x2440x12000	1	1,839	141	25	806	18	3	28	200	30	330	71	29	70	275	322	450	34.5	83	90	79	84	
26300497A	S61150215	S6115303201		8x2440x12000	1	1,839	141	25	806	18	3	28	200	30	330	71	29	70	275	322	450	34.5	83	90	79	84	
26300497A	S61150215	S6115303301		8x2440x12000	1	1,839	141	25	806	18	3	28	200	30	330	71	29	70	275	322	450	34.5	83	90	79	84	
合计(TOTAL):					6	11,034																					

注释 NOTES	<p>L: 熔炼成分 SMELTING COMPOSITION 拉伸标距(GAUGE LENGTH) Lo=5.65 S0 mm A0C冲击试验IMPACT TEST: 0, 纵向LONGITUDINAL, 近表 CLOSE TO SURFACE, 尺寸SIZE10*5*55 CeqA=C+Mn/6</p> <p>B0A01=YIELD STRENGTH B0A02=TENSILE STRENGTH</p> <p>According to EN 10204 3.2</p>	<p>B0A03=PERCENTAGE ELONGATION AFTER FRACTURE A0C01=IMPACT TEST A A0C012=IMPACT TEST B A0C013=IMPACT TEST C A0C02=IMPACT AVERAGE</p>
-------------	--	--

	我们在此证明此材料采用已被认可的方法制造, 并且经检验符合LR船级社规范的要求。 We hereby certify that the material has been made by an approved process and satisfactorily tested in accordance with the Rules of Lloyd 's Register.	技术中心 Technology Center	验船师 SURVEYOR
		郑治龙	 S.J. He Dalian Office Lloyd's Register Classification Society China Co Ltd <small>18021.1.2016.06</small>