MILL'S TEST CERTIFICATION

ÇELSANTAŞ

ACC. TO EN 10204 / 3.1.

SPECIFICATION

HOT ROLLED SECTIONS OF NON-ALLOY STRUCTURAL STEEL
EQUAL ANGLES AND PROFİLES

ACCORDING TO EN 10025-1/2

Inspection No	2024-09/053
Purchase Order	--
Order No	20007643
Invoice No	--
Customer	VALPARASIO
Melting process	E.A.F.
Heat treatment	As-Rolled (AR)

ÇELSANTAŞ ÇELİK MAMÜLLERİ SAN. ve TİC. A.Ş.

HEAD OFFICE / **MILLSHOP**: Kale Köyü Organize Sanayi Bölgesi Mevkii OSB Yolu Cad. No:25 KARABÜK

DATE OF ISSUE: 17.09.2024

TEST RESULTS

Description of Delivery						Tensile Test					Product Analysis (%)								
Section_Symbol	Heat_No	Grade	Waybill_No	Euro Norm for nominal dimensions	Length	Tensile Strength	Yield Point	Elongation	Impact Test Temperature	Impact Test	Chemical Composition (%)								The origin of end product also/country, mill and raw materials
						N/mm²		%	°C Celcius	Joule	C	Mn	Si	S	P	Cu	N	CEQ	
mm	Requirements	-	-	EN	m						%								
NPU 100	10089306	S235JR	--	10279	6	469	309	32	--	--	0,18	0,59	0,14	0,020	0,019	0,020	0,008	0,28	HS CODE: 720711 Place of meting and casting: DUBAI,Facility: RENCORE STEEL TRADING .LLC. Place of hot rolling: TÜRKİYE, Facility: ÇELSANTAŞ ÇELİK MAMULLERİ SAN. Ve TİC. A.Ş.
NPU 120	10089984	S235JR	--	10279	6	442	305	33	--	--	0,16	0,6	0,2	0,022	0,015	0,03	0,008	0,27	HS CODE: 720711 Place of meting and casting: DUBAI,Facility: RENCORE STEEL TRADING .LLC. Place of hot rolling: TÜRKİYE, Facility: ÇELSANTAŞ ÇELİK MAMULLERİ SAN. Ve TİC. A.Ş.
NPU 140	10084409	S235JR	--	10279	6	460	320	32	--	--	0,14	0,65	0,15	0,014	0,014	0,370	0,009	0,31	HS CODE: 720711 Place of meting and casting: TÜRKİYE,Facility: KROMAN ÇELİK SANAYİ A.Ş. Place of hot rolling: TÜRKİYE, Facility: ÇELSANTAŞ ÇELİK MAMULLERİ SAN. Ve TİC. A.Ş.
NPU 140	10089216	S235JR	--	10279	6	445	303	32	--	--	0,16	0,60	0,19	0,013	0,008	0,354	0,008	0,32	HS CODE: 720711 Place of meting and casting: TÜRKİYE,Facility: KROMAN ÇELİK SANAYİ A.Ş. Place of hot rolling: TÜRKİYE, Facility: ÇELSANTAŞ ÇELİK MAMULLERİ SAN. Ve TİC. A.Ş.
NPU 160	10085204	S235JR	--	10279	12	443	302	32	--	--	0,16	0,60	0,15	0,011	0,013	0,021	0,010	0,26	HS CODE: 720711 Place of meting and casting: DUBAI,Facility: RENCORE STEEL TRADING .LLC. Place of hot rolling: TÜRKİYE, Facility: ÇELSANTAŞ ÇELİK MAMULLERİ SAN. Ve TİC. A.Ş.

CE Marking Certificate Number : 2344-CPR-0002

CEQ = C + Mn/6 + (Cr+Mo+V)/15 + (Ni+Cu)/5
CHEMICAL AND MECHANICAL VALUES AND CEV-EQUIVALENT AND U SIGN MATERIAL SUITABLE FOR GALVANIZING I.E. SI-CONTENT 0,031 OR 0,15-0,25 %

CE
2344-CPR-0002

WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATIS FACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.

"We hereby declare that the described goods are processed without incorporating iron and steel products originating in Russia or Belarus and that the described goods are in conformity with EU regulation No. 833/2014 of 31 July 2014 and all subsequent amendments accordingly."

QUALITY MANAGER

ÇELSANTAŞ ÇELİK MAMULLERİ SANAYİ ve TİCARET A.Ş.
Fabrika: Kale Köyü Organize Sanayi Bölgesi Mevkii
Organize Sanayi Yolu Cad. No:25 Merkez Bina Blok No:25 KARABÜK
Merkez: Rüzgarlıbahçe Cad. No: 44 Kavacık/İSTANBUL
B. Müdürlüğü: Tel: 0216 [illegible]676
Mersis No: 0243[illegible]0036760[illegible] Sicil No: 160619
www.celsantas.com.tr