



日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobianidistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE



订货单位 PURCHASER	CUMIC STEEL LIMITED	产品名称 PRODUCT	普通碳素结构钢 General carbon structural steel
收货单位 CONSIGNEE	CUMIC STEEL LIMITED	合同编号 CONTRACT NO.	YGR1ZANN240783010
技术标准/牌号 SPEC/GRADE	ASTM A36/A36M-2019	交货状态 DELIVERY CONDITION	热轧(AR)
车号 TRAIN NO.		签发日期 DATE OF ISSUE	20240821
		质量证明书编号 CERTIFICATE NO.	240821Z00134

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS %													C0A01	C0A02	C0A03	C0A04	B0B01	A0C01	A0C012	A0C013	A0C02
							C	Si	Mn	P	S	CBV	Cr	Mu	V	Ni	Cu	屈服强度 MPa	抗拉强度 MPa	断后伸长率 %	屈服比	弯曲试验 d 3a	冲击值 J	冲击值 J	冲击值 J	冲击值 J		
24406124B	S48180174	S4818317101	75x2000x6000	1	7.065	1	180	202	919	210	83	3.5	48	10	1	210	7	287	447	33.5	0.64	OK	192	197	225	205		
24406124B	S48180174	S4818317102	75x2000x6000	1	7.065	1	180	202	919	210	83	3.5	48	10	1	210	7	287	447	33.5	0.64	OK	192	197	225	205		
合计(TOTAL):				2	14.130																							

注释 NOTES	L: 熔炼成分 SMELTING COMPOSITION 拉伸标距(GAUGE LENGTH) Lo=50 mm A0C冲击试验IMPACT TEST: 20 C, 纵向LONGITUDINAL, 1/4位置 1/4 LOCATION, 尺寸SIZE10*10*55 C0A01=YIELD STRENGTH C0A02=TENSILE STRENGTH C0A03=PERCENTAGE ELONGATION AFTER FRACTURE	C0A04=YIELD STRENGTH RATIO B0B01=BEND TEST A0C01=IMPACT TEST A A0C012=IMPACT TEST B A0C013=IMPACT TEST C A0C02=IMPACT AVERAGE
	According to EN 10204 3.1 本产品已按照标准要求制造和检验, 其结果符合要求, 特此证明。 WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION	



冶金技术处处长
DIRECTOR OF
METALLURGICAL
DEPARTMENT

耿新刚