日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE

订货单位 PURCHASER	HYUNDAI CORPORATION	产品名称 PRODUCT	低合金高强度结构钢 High strength low alloy structural steel		
收货单位 CONSIGNEE	HYUNDAI CORPORATION	合同编号 CONTRACT NO.	YGR1ZANN240583008-01		
技术标准/牌号 SPEC/GRADE	ASTM A572/572M;A572 Gr.50	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20240704
		证书编号 CERTIFICATE NO.	240704Z00474		
车 号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS % C	Si	Mn	P	S	Als	Nb	Cr	Ni	Cu	Mo	V	Ti	CE	B0A01 屈服强度 MPa Rp0.2	B0A02 抗拉强度 MPa Rm	B0A03 断后伸长率 % B5	B0A04 屈强比	B0B01 弯曲试验 d=3a 180°	A0C01 冲击单值 A J	A0C012 冲击单值 B J	A0C013 冲击单值 C J	A0C02 冲击均值 Ave J
							$\times10^{-3}$	$\times10^{-3}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-2}$									
24110763D	S47030056	S4703021201	20x2440x12000	1	4,597	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	402	566	25	0.71	OK	236	215	206	219
24110763D	S47030056	S4703023101	20x2440x12000	1	4,597	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	402	566	25	0.71	OK	236	215	206	219
24110763D	S47030056	S4703023201	20x2440x12000	1	4,597	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	402	566	25	0.71	OK	236	215	206	219
24110763D	S47030057	S4703024101	20x2440x12000	1	4,597	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	377	584	26	0.65	OK	236	207	233	225
24110763D	S47030057	S4703024201	20x2440x12000	1	4,597	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	377	584	26	0.65	OK	236	207	233	225
24110761D	S47030058	S4703025101	25x2440x12000	1	5,746	L	157	215	1404	220	33	40	130	68	200	9	30	2	130	41	412	557	26	0.74	OK	223	217	237	226
24110761D	S47030058	S4703025201	25x2440x12000	1	5,746	L	157	215	1404	220	33	40	130	68	200	9	30	2	130	41	412	557	26	0.74	OK	223	217	237	226
24110761D	S47030058	S4703026201	25x2440x12000	1	5,746	L	157	215	1404	220	33	40	130	68	200	9	30	2	130	41	412	557	26	0.74	OK	223	217	237	226
24110761D	S47030058	S4703027101	25x2440x12000	1	5,746	L	157	215	1404	220	33	40	130	68	200	9	30	2	130	41	412	557	26	0.74	OK	223	217	237	226
24110761D	S47030058	S4703027201	25x2440x12000	1	5,746	L	157	215	1404	220	33	40	130	68	200	9	30	2	130	41	412	557	26	0.74	OK	223	217	237	226
24110763D	S47030059	S4703028101	25x2440x12000	1	5,746	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	435	563	25	0.77	OK	224	219	205	216
24110763D	S47030059	S4703028201	25x2440x12000	1	5,746	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	435	563	25	0.77	OK	224	219	205	216
			合计(TOTAL):	12	63,207																								

注释 NOTES

L: 熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACTTEST: 4℃, 纵向LONGITUDINAL, 近表 CLOSE TO SURFACE, 尺寸SIZE10*10*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PRECENTAGE ELONGATION AFTER FRACTURE
B0A04=YIELD STRENGTH RATIO
B0B01=BENDTEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

野牛

本产品已按照标准要求进行制造和检验，其结果符合要求，特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION

冶金技术处处长
DIRECTOR OF METALLURGICAL DEPARTMENT