Contract No.	Z240304108
Customer	HYUNDAI CORPORATION
PO No.	F240300299
L/C No.	L0696240600491
Commodity	**H-BEAM**
Specification	**ASTM A572 G50/A992/CSA G40.21-13 50WM(345WM)**

INSPECTION CERTIFICATE

EN 10204(2004) TYPE 3.1

HYUNDAI STEEL

WWW.HYUNDAI-STEEL.COM PAGE: [1 / 1]

Factory	63, Jungbong-Daero, Dong-gu, Incheon, S. Korea
Certificate No.	IH20240500324-1
Class certificate No.	
Issue date	2024-07-01

Dimensions	Length	Heat No.	Quantity (PCS)	Weight (kg)	Chemical Composition																		Tensile Test			Yield Ratio (3)	BEND TEST	Impact Test(L) V-Notch ℃				Remarks (Impact Specimen Size)	Country of Melt and Pour
					C	Si	Mn	P	S	Cu	Ni	Mo	Cr	Al	V	Nb	N	CE(1)					Tensile Strength	Yield Strength	Elongation (2)			AVG	1	2	3		
					×100			×1000		×100				×1000			×10000	×100					N/mm2		%	-	-	-					
8X4X15	12.00 M	D 175911	1	268	16	14	62	28	5	25	9	2	15	3	2	16	87	32					533 534	438 423	24.0 24.6	0.822 0.793								KOR
8X4X15	12.00 M	D 181219	24	6,432	17	15	63	24	4	23	9	2	12	4	2	18	154	32					547 547	429 437	23.6 24.4	0.785 0.799								KOR
TOTAL			25	6,700	====== E N D ======																												

(1) Ceq: (CE=C+(Cr+V+Mo)/5+(Cu+Ni)/15+Mn/6)
(2) Gauge length : 200 mm
(3) Y.R = Y.S/T.S

Note
Melted and Poured in Republic of Korea
Country of Produce and Process - Republic of Korea
HSCODE(H Section) : 7216.33

WE HEREBY CERTIFY THAT THE MATERIAL HAS BEEN MADE AND TESTED IN ACCORDANCE WITH THE ABOVE SPECIFICATION AND ALSO WITH THE REQUIREMENTS CALLED FOR THE ABOVE ORDER.

지태훈

General Manager of Q.A Team

This test report can be verified the authenticity to scan the top-right QR code via 'Qreal' mobile app.

2024.07.01.10:20:57 9201675 HMS I 102(A)-3a A4(210x297)

※ 현대제철은 검사증명서를 사본으로 제출하지 않습니다. 사본일 경우, 현대제철 각 영업소로 확인하시기 바랍니다. 문의)02-772-2125