日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE

订货单位 PURCHASER	CUMIC STEEL LIMITED	产品名称 PRODUCT	普通碳素结构钢 General carbon structural steel		
收货单位 CONSIGNEE	CUMIC STEEL LIMITED	合同编号 CONTRACT NO.	YGR1ZANN240683004-02		
技术标准/牌号 SPEC/GRADE	ASTM A36/A36M;ASTM A36	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20240729
		证明书编号 CERTFICATE NO.	240729Z00288		
车 号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS % C	Si	Mn	P	S	CEV	Cr	Mo	V	Ni	Cu	Nb	Ti	B 0A01 屈服强度 MPa Rp0.2	B 0A02 抗拉强度 MPa Rm	B 0A03 断后伸长率 % B5	B 0A04 屈强比	B 0B01 弯曲试验 d=3a 180°	A 0C01 冲击单值 A J	A 0C012 冲击单值 B J	A 0C013 冲击单值 C J	A 0C02 冲击均值 Ave J
							$\times10^{-3}$	$\times10^{-3}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$	$\times10^{-2}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$										
24111563D	2476266	24G5349001	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	278	468	28	0.59	OK	216	208	235	220
24111563D	2476266	24G5349002	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	278	468	28	0.59	OK	216	208	235	220
24111563D	2476266	24G5349003	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	278	468	28	0.59	OK	216	208	235	220
24111563D	2476266	24G5349004	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	278	468	28	0.59	OK	216	208	235	220
24111563D	2475568	24G5350001	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	284	468	26.5	0.61	OK	166	191	190	182
24111563D	2475568	24G5350002	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	284	468	26.5	0.61	OK	166	191	190	182
24111563D	2475568	24G5350003	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	284	468	26.5	0.61	OK	166	191	190	182
24111563D	2475568	24G5350004	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	284	468	26.5	0.61	OK	166	191	190	182
24111563D	2475568	24G5407001	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	284	468	26.5	0.61	OK	166	191	190	182
24111563D	2475568	24G5407002	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	284	468	26.5	0.61	OK	166	191	190	182
24111563D	2476266	24G5407003	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	278	468	28	0.59	OK	216	208	235	220
24111563D	2476266	24G5407004	20x2440x12000	1	4,597	L	171	203	855	210	67	32	38	60	2	140	9	20	30	278	468	28	0.59	OK	216	208	235	220
			合计(TOTAL):	12	55,164																							

注释 NOTES

L：熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACT TEST：20℃，纵向LONGITUDINAL，
近表 CLOSE TO SURFACE，尺寸SIZE10*10*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PRECENTAGE ELONGATION AFTER FRACTURE
B0A04=YIELD STRENGTH RATIO
B0B01=BEND TEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

野牛

本产品已按照标准要求进行制造和检验，其结果符合要求，特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION

冶金技术处处长
DIRECTOR OF METALLURGICAL DEPARTMENT