



敬业 (营口) 中板有限公司
JINGYE (YINGKOU) MEDIUM PLATE CO.LTD.

辽宁省营口市老边区冶金街/115005

Yejinstreet, Laobiandistrict, Yingkou, Liaoning, P.R.China/115005

TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE



订货单位 PURCHASER	PRODALAM SA	产品名称 PRODUCT	低合金高强度结构钢 High strength low alloy structural steel		
收货单位 CONSIGNEE	PRODALAM SA	合同编号 CONTRACT NO.	YGCAZANN250483008-03		
技术标准/牌号 SPEC/GRADE	ASTM A572/A572M-2021 ; A572 Gr.50	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20250520
		证明书编号 CERTIFICATE NO.	250520Z01054	是否保性能 GUARANTEE OR NOT	是 YES
车号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS %																B0A01	B0A02	B0A03	B0A04	B0B01	A0C01	A0C012	A0C013	A0C02		
							C	Si	Mn	P	S	Als	Nb	Cr	Ni	Cu	Mo	V	Ti	CE	屈服强度	抗拉强度	断后伸长率	屈强比	弯曲试验	冲击单值 A	冲击单值 B	冲击单值 C	冲击均值 Ave				
							x10 ⁻³	x10 ⁻³	x10 ⁻³	x10 ⁻⁴	x10 ⁻⁴	x10 ⁻³	x10 ⁻⁴	x10 ⁻²	MPa	MPa	%		d=3a	J	J	J	J										
25204527C	2553852	25E8811002	12x2440x12000	1	2,758	L	152	190	1464	190	42	24	180	110	320	13	20	2	110	42	408	552	24	0.74	OK	157	149	110	139				
合计(TOTAL):				1	2,758																												

注释
NOTES

L : 熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACTTEST : 4 , 纵向LONGITUDINAL , 近表 CLOSE TO SURFACE , 尺寸SIZE10*10*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PERCENTAGE ELONGATION AFTER FRACTURE

B0A04=YIELD STRENGTH RATIO
B0B01=BENDTEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

本产品已按照标准要求制造和检验, 其结果符合要求, 目视及尺寸检验均符合标准要求, 特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION Both BOTH VISUAL AND DIMENSIONAL INSPECTION MEET THE STANDARD REQUIREMENTS

冶金技术处处长
DIRECTOR OF METALLURGICAL DEPARTMENT

野牛
野牛

殷新刚