



日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE



订货单位 PURCHASER	CUMIC STEEL LIMITED	普通碳素结构钢 General carbon structural steel
收货单位 CONSIGNEE	CUMIC STEEL LIMITED	YGR1ZANN240783010
技术标准/牌号 SPEC/GRADE	ASTM A36/A36M-2019	热轧(AR)
车号 TRAIN NO.		20240826
		240826Z00058



炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析 区域 AA	化学成分 CHEMICAL ANALYSIS %														B0A01	B0A02	B0A03	B0A04	B0B01	A0C01	A0C012	A0C013	A0C02		
							C	Si	Mn	P	S	CrV	Cr	Mo	V	Nb	Cu	Ni	Ti	屈服强度	抗拉强度	断后伸长率	屈服比	冲击试验	冲击值 A	冲击值 B	冲击值 C	冲击平均值			
24406300C	S48230083	S4824266101	10x2440x12000	1	2.298	1.	145	146	823	220	72	30	55	40	1	340	8	30	40	293	446	25.5	0.66	OK	148	140	139	142			
24406300C	S48230083	S4824266201	10x2440x12000	1	2.298	1.	145	146	823	220	72	30	55	40	1	340	8	30	40	293	446	25.5	0.66	OK	148	140	139	142			
24406300C	S48230083	S4824266301	10x2440x12000	1	2.298	1.	145	146	823	220	72	30	55	40	1	340	8	30	40	293	446	25.5	0.66	OK	148	140	139	142			
合计(TOTAL):				3	6.894																										

注释 NOTES	L: 熔炼成分 SMELTING COMPOSITION 拉伸标距(GAUGE LENGTH) Lo=200 mm A0C冲击试验IMPACT TEST: 20 C, 纵向LONGITUDINAL, 近表 CLOSE TO SURFACE, 尺寸SIZE10*7.5*55 B0A01=YIELD STRENGTH B0A02=TENSILE STRENGTH B0A03=PERCENTAGE ELONGATION AFTER FRACTURE	B0A04=YIELD STRENGTH RATIO B0B01=BEND TEST A0C01=IMPACT TEST A A0C012=IMPACT TEST B A0C013=IMPACT TEST C A0C02=IMPACT AVERAGE
	According to EN 10204 3.1	
	本产品已按照标准要求制造和检验, 其结果符合要求, 特此证明。 WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION	



冶金技术处处长
DIRECTOR OF
METALLURGICAL
DEPARTMENT
耿新刚