日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE

订货单位 PURCHASER	CUMIC STEEL LIMITED	产品名称 PRODUCT	普通碳素结构钢 General carbon structural steel		
收货单位 CONSIGNEE	CUMIC STEEL LIMITED	合同编号 CONTRACT NO.	YGR1ZANN240485002-05		
技术标准/牌号 SPEC/GRADE	ASTM A36/A36M-2019	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20240604
		证明书编号 CERTFICATE NO.	240604Z00398		
车 号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS % C	Si	Mn	P	S	CEV	Cr	Mo	V	Ni	Cu	Nb	Ti	B0A01 屈服强度 MPa Rp0.2	B0A02 抗拉强度 MPa Rm	B0A03 断后伸长率 % B5	B0A04 屈强比	B0B01 弯曲试验 d=3a 180°	A0C01 冲击单值A J	A0C012 冲击单值B J	A0C013 冲击单值C J	A0C02 冲击均值Ave J
							$\times10^{-3}$	$\times10^{-3}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$	$\times10^{-2}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$									
24203787A	S45260192	S4526346101	6x2440x12000	1	1,379	L	132	156	826	180	101	30	117	10	1	420	6	20	20	310	453	25.5	0.68	OK	67	84	79	77
24203787A	S45260193	S4526360101	6x2440x12000	1	1,379	L	132	156	826	180	101	30	117	10	1	420	6	20	20	315	447	27	0.70	OK	84	78	80	81
24203787A	S45260193	S4526360301	6x2440x12000	1	1,379	L	132	156	826	180	101	30	117	10	1	420	6	20	20	315	447	27	0.70	OK	84	78	80	81
24203787A	S45260193	S4526365301	6x2440x12000	1	1,379	L	132	156	826	180	101	30	117	10	1	420	6	20	20	315	447	27	0.70	OK	84	78	80	81
24203787A	S45260194	S4526370101	6x2440x12000	1	1,379	L	132	156	826	180	101	30	117	10	1	420	6	20	20	314	449	26.5	0.70	OK	81	88	83	84
24203787A	S45260194	S4526370201	6x2440x12000	1	1,379	L	132	156	826	180	101	30	117	10	1	420	6	20	20	314	449	26.5	0.70	OK	81	88	83	84
24203788A	S45290127	S4529172101	6x2440x12000	1	1,379	L	137	140	836	170	115	30	89	20	1	440	9	20	20	319	443	23.5	0.72	OK	80	76	79	78
24203788A	S45290127	S4529172201	6x2440x12000	1	1,379	L	137	140	836	170	115	30	89	20	1	440	9	20	20	319	443	23.5	0.72	OK	80	76	79	78
24203788A	S45290127	S4529172301	6x2440x12000	1	1,379	L	137	140	836	170	115	30	89	20	1	440	9	20	20	319	443	23.5	0.72	OK	80	76	79	78
24203788A	S45290127	S4529175101	6x2440x12000	1	1,379	L	137	140	836	170	115	30	89	20	1	440	9	20	20	319	443	23.5	0.72	OK	80	76	79	78
24203788A	S45290127	S4529175201	6x2440x12000	1	1,379	L	137	140	836	170	115	30	89	20	1	440	9	20	20	319	443	23.5	0.72	OK	80	76	79	78
24203788A	S45290127	S4529175301	6x2440x12000	1	1,379	L	137	140	836	170	115	30	89	20	1	440	9	20	20	319	443	23.5	0.72	OK	80	76	79	78
			合计(TOTAL)：	12	16,548																							

注释 NOTES

L：熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACTTEST：20°C，纵向LONGITUDINAL，近表 CLOSE TO SURFACE，尺寸SIZE10*5*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PRECENTAGE ELONGATION AFTER FRACTURE
B0A04=YIELD STRENGTH RATIO
B0B01=BENDTEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

野牛

本产品已按照标准要求进行制造和检验，其结果符合要求，特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION

冶金技术处处长
DIRECTOR OF METALLURGICAL DEPARTMENT