



产品质量证明书 INSPECTION CERTIFICATE

公司名称: 冠县众冠新材料有限公司

地址: 中国山东聊城冠县新世纪工业园

COMPANY NAME: GUANXIAN ZHONGGUAN NEW MATERIALS CO., LTD.

Address: Guan Xian industry Park, Liaocheng, Shandong, China

订货单位 CUSTOMER		SAMSUNG C&T CORPORATION							钢号 STEEL GRADE		CS-B		产品名称 PRODUCT		HOT DIPPED GALVANIZED STEEL IN SHEET		
收货单位 PURCHASER		SAMSUNG C&T CORPORATION											签发日期 DATE OF ISSUE		2026-3-12		
标准 SPECIFICATION		ASTM A653											合同号 CONTRACT NO.		VS202512307054		
卷号 Coil No.	重量 WEIGHT	片数	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating		镀层质量 coating mass (g/m²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn		C	Si	Mn	P	S	R _{el} (N/mm²)	R _m (N/mm²)	A (%)	HRB
7054-2-212	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	183	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64
7054-2-213	1.908	220	0.35*1000*3000	Chromated	72h	0.5	99.5	183	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64
7054-2-214	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	184	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-215	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	184	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-216	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-217	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-218	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-219	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-220	1.900	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64
7054-2-221	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64
7054-2-222	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-223	1.902	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-224	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-225	1.902	220	0.35*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-226	1.902	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-227	1.902	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-228	1.900	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-229	1.888	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-230	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	184	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-231	1.916	220	0.35*1000*3000	Chromated	72h	0.5	99.5	184	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-232	1.908	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64
7054-2-204	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64
7054-2-205	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-206	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-207	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64
7054-2-208	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	25.5	64

质量部
(2)

卷号 Coil No.	重量 WEIGHT	片数	成品规格 Size(mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating		镀层质量 coating mass(g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn		C	Si	Mn	P	S	R _{el} (N/mm ²)	R _m (N/mm ²)	A(%)	HRB
7054-2-209	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-210	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-2-211	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-233	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-234	1.900	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-235	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-236	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-237	1.902	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	330	395	26	65
7054-2-238	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-239	1.908	220	0.35*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	315	385	29	63
7054-2-240	1.908	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	324	390	27.5	64
7054-2-241	1.912	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	324	390	27.5	64
7054-2-242	1.912	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	330	395	26	65
7054-2-243	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	330	395	26	65
7054-2-244	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	315	385	29	63
7054-2-245	1.898	220	0.35*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	315	385	29	63
7054-2-246	1.906	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	330	395	26	65
7054-2-247	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	330	395	26	65
7054-2-248	1.898	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	315	385	29	63
7054-2-249	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	315	385	29	63
7054-2-250	1.904	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	325	390	25.5	64
7054-2-251	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	325	390	25.5	64
7054-2-252	1.908	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	324	390	27.5	64
7054-2-253	1.908	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	324	390	27.5	64
7054-2-254	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	330	395	26	65
7054-2-255	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	330	395	26	65
7054-2-256	1.910	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	315	385	29	63
7054-2-257	1.912	220	0.35*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	315	385	29	63
7054-1-258	1.240	140	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-1-259	1.136	129	0.35*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	324	390	27.5	64
7054-1-271	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-272	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-273	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-274	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-275	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	329	395	26	65
7054-1-276	1.932	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	329	395	26	65
7054-1-277	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-278	1.936	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-279	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-280	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	325	390	26	64




卷号 Coil No.	重量 WEIGHT	片数	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating		镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn		C	Si	Mn	P	S	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
7054-1-281	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-282	1.936	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-283	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-284	1.950	195	0.4*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-285	1.932	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-286	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-287	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-288	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-289	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-290	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-291	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-292	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-293	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-294	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-295	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	316	385	29	63
7054-1-296	1.956	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	316	385	29	63
7054-1-297	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	329	395	31	65
7054-1-298	1.960	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	329	395	31	65
7054-1-299	1.948	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	326	390	27.5	64
7054-1-300	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	326	390	27.5	64
7054-1-301	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	325	390	26	64
7054-1-302	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	325	390	26	64
7054-1-303	1.944	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-304	1.944	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-305	1.944	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-306	1.954	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-307	1.946	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-308	1.944	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-309	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-310	1.944	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-311	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-312	1.948	195	0.4*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-313	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-314	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-315	1.946	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-316	1.944	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-317	1.946	195	0.4*1000*3000	Chromated	72h	0.5	99.5	184	0.038	0.01	0.16	0.008	0.008	325	390	26	64
7054-1-318	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	184	0.038	0.01	0.16	0.008	0.008	325	390	26	64
7054-1-319	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	316	385	29	63
7054-1-320	1.936	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	316	385	29	63

卷号 Coil No.	重量 WEIGHT	片数	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating		镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn		C	Si	Mn	P	S	R _{eL} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
7054-1-321	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	329	395	31	65
7054-1-322	1.936	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	329	395	31	65
7054-1-323	1.934	195	0.4*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	326	390	27.5	64
7054-1-324	1.938	195	0.4*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	326	390	27.5	64
7054-1-325	1.932	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-326	1.942	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	385	29	63
7054-1-327	1.932	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-328	1.926	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	329	395	31	65
7054-1-329	1.934	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-330	1.940	195	0.4*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	326	390	27.5	64
7054-1-331	1.936	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-332	1.958	195	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-1-333	1.464	146	0.4*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	325	390	26	64
7054-132	1.838	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-133	1.840	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-134	1.840	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-135	1.842	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-136	1.838	151	0.5*1000*3000	Chromated	72h	0.5	99.5	188	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-137	1.840	151	0.5*1000*3000	Chromated	72h	0.5	99.5	188	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-138	1.834	151	0.5*1000*3000	Chromated	72h	0.5	99.5	188	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-139	1.840	151	0.5*1000*3000	Chromated	72h	0.5	99.5	188	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-140	1.844	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	318	357	36	54
7054-141	1.846	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	318	357	36	54
7054-142	1.846	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	318	357	36	54
7054-143	1.850	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	318	357	36	54
7054-144	1.848	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	322	361	32	56
7054-145	1.844	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	322	361	32	56
7054-146	1.846	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	322	361	32	56
7054-147	1.844	151	0.5*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	322	361	32	56
7054-148	1.840	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-149	1.816	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-260	1.810	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-261	1.814	151	0.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	319	353	35	53
7054-262	1.808	151	0.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-263	1.788	151	0.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-264	1.796	151	0.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-265	1.796	151	0.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	321	360	31	55
7054-266	1.800	151	0.5*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	318	357	36	54
7054-267	1.802	151	0.5*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	318	357	36	54
7054-268	1.780	151	0.5*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	318	357	36	54



卷号 Coil No.	重量 WEIGHT	片数	成品规格 Size(mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分(%) The composition of coating		镀层质量 coating mass(g/m ²)	化学成分 CHEMICAL COMPOSITION(%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn		C	Si	Mn	P	S	R _{el} (N/mm ²)	R _m (N/mm ²)	A(%)	HRB
7054-269	1.414	116	0.5*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	318	357	36	54
7054-150	1.862	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-151	1.852	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-152	1.856	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-153	1.860	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-154	1.864	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-155	1.858	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-156	1.858	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-157	1.860	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-158	1.864	77	1*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-159	1.864	77	1*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-160	1.854	77	1*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-161	1.854	77	1*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-162	1.854	77	1*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	332	368	37	57
7054-163	1.854	77	1*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	332	368	37	57
7054-164	1.854	77	1*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	332	368	37	57
7054-165	1.856	77	1*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	332	368	37	57
7054-166	1.858	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-167	1.860	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-168	1.854	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-169	1.858	77	1*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	331	369	37	57
7054-170	1.856	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-171	1.856	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-172	1.856	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-173	1.862	77	1*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	322	360	39	56
7054-174	1.860	77	1*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-175	1.864	77	1*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-176	1.506	62	1*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-177	1.838	51	1.5*1000*3000	Chromated	72h	0.5	99.5	187	0.036	0.01	0.17	0.0075	0.007	330	370	36	58
7054-178	1.832	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	300	346	38	53
7054-179	1.836	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	300	346	38	53
7054-180	1.830	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	300	346	38	53
7054-181	1.834	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	315	361	38	56
7054-182	1.840	51	1.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	315	361	38	56
7054-183	1.832	51	1.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	315	361	38	56
7054-184	1.830	51	1.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	315	361	38	56
7054-185	1.834	51	1.5*1000*3000	Chromated	72h	0.5	99.5	184	0.036	0.01	0.17	0.0075	0.007	306	350	35	54
7054-186	1.846	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	306	350	35	54
7054-187	1.836	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	306	350	35	54
7054-188	1.840	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	306	350	35	54



卷号 Coil No.	重量 WEIGHT	片数	成品规格 Size (mm)	表面处理 surface treatment	盐雾试验 salt spray test	镀层成分 (%) The composition of coating		镀层质量 coating mass (g/m ²)	化学成分 CHEMICAL COMPOSITION (%)					力学性能 MECHANIC PROPERTIES			
						Al	Zn		C	Si	Mn	P	S	R _{el} (N/mm ²)	R _m (N/mm ²)	A (%)	HRB
7054-189	1.836	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	360	37	56
7054-190	1.836	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	316	360	37	56
7054-191	1.840	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	316	360	37	56
7054-192	1.838	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	316	360	37	56
7054-193	1.838	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	315	361	38	56
7054-194	1.832	51	1.5*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	315	361	38	56
7054-195	1.836	51	1.5*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	315	361	38	56
7054-196	1.834	51	1.5*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	315	361	38	56
7054-197	1.840	51	1.5*1000*3000	Chromated	72h	0.5	99.5	188	0.038	0.01	0.16	0.008	0.008	306	350	35	54
7054-198	1.828	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	306	350	35	54
7054-199	1.842	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	306	350	35	54
7054-200	1.840	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	306	350	35	54
7054-201	1.840	51	1.5*1000*3000	Chromated	72h	0.5	99.5	186	0.036	0.01	0.17	0.0075	0.007	316	360	37	56
7054-202	1.838	51	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	360	37	56
7054-203	1.592	44	1.5*1000*3000	Chromated	72h	0.5	99.5	185	0.038	0.01	0.16	0.008	0.008	316	360	37	56
	376.986																

NOTE: 1、ReL : lower yield strength Rm : tensile strength A: percentage elongation after fracture

2、1 N/mm²=1 MPa

证明本表所列制品，均依材料规格制造及试验，并符合规格之要求

WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED HEREIN HAS BEEN MANUFACTURED AND TESTED WITH SATISFACTORY RESULT IN ACCORDANCE WITH THE REQUIREMENT OF THE ABOVE MATERIAL SPECIFICATION.

质量负责人

QUALITY MANAGER

张同静

质量部
(2)