



日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE



订货单位 PURCHASER	HYUNDAI CORPORATION	低合金高强度结构钢 High strength low alloy structural steel	
收货单位 CONSIGNEE	HYUNDAI CORPORATION	YGR1ZANN240583008-01	
技术标准/牌号 SPEC/GRADE	ASTM A572/572M;A572 Gr.50	热轧(AR)	签发日期 DATE OF ISSUE
		20240704	
车号 TRAIN NO.	240704Z00475		

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析 区域 AA	化学成分 CHEMICAL ANALYSIS %														B0A01 屈服 强度 MPa Rp0.2	B0A02 抗 拉 强度 MPa Rm	B0A03 断 后 伸 长 率 %	B0A04 屈 强 比	B0B01 弯 曲 试 验 d=3a 180°	A0C01 冲击 单 值 J	A0C012 冲击 单 值 J	A0C013 冲击 单 值 J	A0C02 冲击 均 值 J
							C	Si	Mn	P	S	Als	Nb	Cr	Ni	Cu	Mo	V	Ti	CE									
							$\times 10^{-3}$	$\times 10^{-3}$	$\times 10^{-3}$	$\times 10^{-4}$	$\times 10^{-4}$	$\times 10^{-3}$																	
24110763D	S47030060	S4703032101	25x2440x12000	1	5,746	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	401	554	25.5	0.72	OK	234	237	212	228
24110763D	S47030060	S4703032201	25x2440x12000	1	5,746	L	162	216	1380	230	31	21	130	73	220	8	30	2	130	41	401	554	25.5	0.72	OK	234	237	212	228
合计(TOTAL):				2	11,492																								

注释
NOTES

L: 熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACT TEST: 4C, 纵向LONGITUDINAL, 近表 CLOSE TO SURFACE, 尺寸SIZE10*10*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PERCENTAGE ELONGATION AFTER FRACTURE

B0A04=YIELD STRENGTH RATIO
B0B01=BEND TEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

野牛

本产品已按照标准要求进行制造和检验, 其结果符合要求, 特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION

冶金技术处处长
DIRECTOR OF METALLURGICAL DEPARTMENT

耿新刚