敬业（营口）中板有限公司
JINGYE (YINGKOU) MEDIUM PLATE CO.LTD.
辽宁省营口市老边区冶金街/115005 NO.:DT2101501/A
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 0311-966666 FAX:0417-3256057

产品质量证明书
INSPECTION CERTIFICATE

敬业(营口)中板有限公司 质量专用章

订货单位 PURCHASER	SAMSUNG C&T CORPORATION	产品名称 PRODUCT	低合金高强度结构钢 High strength low alloy structural steel		
收货单位 CONSIGNEE	SAMSUNG C&T CORPORATION	合同编号 CONTRACT NO.	YGCAZANN260383004-01		
技术标准/牌号 SPEC/GRADE	ASTM A572/572M;A572 Gr.50	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20260530
		证明书编号 CERTIFICATE NO.	260530Z00246	是否保性能 GUARANTEE OR NOT	是 YES
车 号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS % C	Si	Mn	P	S	Als	Nb	Cr	Ni	Cu	Mo	V	Ti	CE	B0A01 屈服强度 MPa Rp0.2	B0A02 抗拉强度 MPa Rm	B0A03 断后伸长率 % B5	B0A04 屈强比	B0B01 弯曲试验 d=3a 180°	A0C01 冲击单值A J	A0C012 冲击单值B J	A0C013 冲击单值C J	A0C02 冲击均值Ave J
							$\times10^{-3}$	$\times10^{-3}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-2}$									
26305419D	S65230239	S6523322101	16x2440x12000	1	3,678	L	162	193	1380	190	81	30	130	65	270	7	80	2	120	41	426	541	23.5	0.79	OK	190	151	152	164
26305419D	S65230239	S6523322301	16x2440x12000	1	3,678	L	162	193	1380	190	81	30	130	65	270	7	80	2	120	41	426	541	23.5	0.79	OK	190	151	152	164
26305419D	S65230239	S6523323101	16x2440x12000	1	3,678	L	162	193	1380	190	81	30	130	65	270	7	80	2	120	41	426	541	23.5	0.79	OK	190	151	152	164
26305419D	S65230239	S6523323201	16x2440x12000	1	3,678	L	162	193	1380	190	81	30	130	65	270	7	80	2	120	41	426	541	23.5	0.79	OK	190	151	152	164
26305419D	S65230239	S6523323301	16x2440x12000	1	3,678	L	162	193	1380	190	81	30	130	65	270	7	80	2	120	41	426	541	23.5	0.79	OK	190	151	152	164
26305419D	S65230246	S6523340301	14x2440x12000	1	3,218	L	162	193	1380	190	81	30	130	65	270	7	80	2	120	41	374	521	26.5	0.72	OK	194	167	173	178
			合计(TOTAL)：	6	21,608																								

注释 NOTES

L：熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACTTEST：4°C，纵向LONGITUDINAL，近表 CLOSE TO SURFACE，尺寸SIZE10*10*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PRECENTAGE ELONGATION AFTER FRACTURE
B0A04=YIELD STRENGTH RATIO
B0B01=BENDTEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

野牛

本产品已按照标准要求进行制造和检验，其结果符合要求，目视及尺寸检验均符合标准要求，特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION Both BOTH VISUAL AND DIMENSIONAL INSPECTION MEET THE STANDARD REQUIREMENTS

技术中心
Technology Center

郑治龙