日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE

订货单位 PURCHASER	SAMSUNG C&T CORPORATION	产品名称 PRODUCT	普通碳素结构钢 General carbon structural steel		
收货单位 CONSIGNEE	SAMSUNG C&T CORPORATION	合同编号 CONTRACT NO.	YGCAZANN241083007-05		
技术标准/牌号 SPEC/GRADE	ASTM A36/A36M ; ASTM A36	交货状态 DELIVERY CONDITION	热轧(AR)	签发日期 DATE OF ISSUE	20241123
		证明书编号 CERTIFICATE NO.	241123Z00025		
车 号 TRAIN NO.					

炉号 HEAT NO.	批号 LOT NO.	钢板号 PLATE NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	分析区域 AA	化学成分 CHEMICAL ANALYSIS % C	Si	Mn	P	S	CEV	Cr	Mo	V	Ni	Cu	Nb	Ti	B0A01 屈服强度 MPa Rp0.2	B0A02 抗拉强度 MPa Rm	B0A03 断后伸长率 % B5	B0A04 屈强比	B0B01 弯曲试验 d=3a 180°	A0C01 冲击单值A J	A0C012 冲击单值B J	A0C013 冲击单值C J	A0C02 冲击均值Ave J
							$\times10^{-3}$	$\times10^{-3}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$	$\times10^{-2}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-3}$	$\times10^{-4}$	$\times10^{-4}$									
24209829A	24X5604	24L8079001	14x2440x12000	1	3,218	L	183	197	832	240	42	33	36	30	1	100	13	30	40	299	470	27.5	0.64	OK	151	155	159	155
24209829A	24X5604	24L8079002	14x2440x12000	1	3,218	L	183	197	832	240	42	33	36	30	1	100	13	30	40	299	470	27.5	0.64	OK	151	155	159	155
24121307A	24X5600	24L8080004	28x2440x12000	1	6,436	L	199	217	846	160	74	35	31	20	1	100	11	20	30	313	480	24	0.65	OK	131	129	141	134
24209829A	24X5604	24L8092001	14x2440x12000	1	3,218	L	183	197	832	240	42	33	36	30	1	100	13	30	40	299	470	27.5	0.64	OK	151	155	159	155
24209829A	24X5604	24L8092002	14x2440x12000	1	3,218	L	183	197	832	240	42	33	36	30	1	100	13	30	40	299	470	27.5	0.64	OK	151	155	159	155
24209830A	24X5624	24L8101001	28x2440x12000	1	6,436	L	170	202	822	200	79	32	32	30	1	130	12	20	20	297	461	27	0.64	OK	135	122	199	152
24209830A	24X5624	24L8238001	28x2440x12000	1	6,436	L	170	202	822	200	79	32	32	30	1	130	12	20	20	297	461	27	0.64	OK	135	122	199	152
			合计(TOTAL)：	7	32,180																							

注释 NOTES

L：熔炼成分 SMELTING COMPOSITION
拉伸标距(GAUGE LENGTH) Lo=200 mm
A0C冲击试验IMPACTTEST：20°C，纵向LONGITUDINAL，近表 CLOSE TO SURFACE，尺寸SIZE10*10*55
B0A01=YIELD STRENGTH
B0A02=TENSILE STRENGTH
B0A03=PRECENTAGE ELONGATION AFTER FRACTURE
B0A04=YIELD STRENGTH RATIO
B0B01=BENDTEST
A0C01=IMPACT TEST A
A0C012=IMPACT TEST B
A0C013=IMPACT TEST C
A0C02=IMPACT AVERAGE

According to EN 10204 3.1

本产品已按照标准要求进行制造和检验，其结果符合要求，特此证明。
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HAS MANUFACTURED AND TESTED WITH SATISFACTORY RESULTS IN ACCORDANCE WITH THE REQUIREMENTS OF THE ABOVE MATERIAL SPECIFICATION

野牛

冶金技术处处长
DIRECTOR OF METALLURGICAL DEPARTMENT