



日钢营口中板有限公司
RIZHAO STEEL YINGKOU MEDIUM PLATE CO.,LTD.
辽宁省营口市老边区冶金街/115005
Yejinstreet,Laobiandistrict,Yingkou,Liaoning,P.R.China/115005
TEL:0417-3256081 FAX:0417-3256057 NO.:DT2101501/A

产品质量证明书
INSPECTION CERTIFICATE



订货单位 PURCHASER	CUMIC STEEL LIMITED		船川钢板 Hull Steel plate	
收货单位 CONSIGNEE	CUMIC STEEL LIMITED		YGRIZANN240783010-03	
技术标准/牌号 SPEC/GRADE	LR RULES ; LRB		正火轧制(NR) 240907Z00500	签发日期 DATE OF ISSUE 20240910
车号 TRAINNO.				控制号 CONTROL NUMBER DLN2401120

炉号 HEATNO.	批号 LOTNO.	钢板号 PLATE NO.	分段号 SECTION NO.	规格 (MM) DIMENSION	数量 QTY	重量 WEIGHT kg	化学成分 CHEMICAL ANALYSIS %																	力学性能			
							C	Si	Mn	P	S	Als	Ti	Nb	Na	Cr	Cu	Mu	CeqA	B0A01 屈服强度 ReH	B0A02 抗拉强度 Rm	B0A03 断后伸长率 B1	A0C01 冲击值 J	A0C012 冲击值 J	A0C013 冲击值 J	A0C02 平均冲击值 Ave	
24206700A	S48290240	S4829369101		6x2440x12000	1	1.379	140	22	861	12	5	27	160	20	200	28	10	10	284	364	465	32	83	89	94	89	
24206700A	S48290240	S4829369201		6x2440x12000	1	1.379	140	22	861	12	5	27	160	20	200	28	10	10	284	364	465	32	83	89	94	89	
24206700A	S48290240	S4829369301		6x2440x12000	1	1.379	140	22	861	12	5	27	160	20	200	28	10	10	284	364	465	32	83	89	94	89	
合计(TOTAL):					3	4.137																					

<p>注释 NOTES</p> <p>L: 熔炼成分 SMELTING COMPOSITION 拉伸标距(GAUGE LENGTH) Lo=5.65√S0 mm A0C冲击试验IMPACT TEST: 0 C, 纵向LONGITUDINAL, 近表 CLOSE TO SURFACE, 尺寸SIZE10*5*55 CeqA=C+Mn/6 B0A01=YIELD STRENGTH B0A02=TENSILE STRENGTH</p> <p>According to EN 10204 3.2 我们在此证明此材料采用已被认可的方法制造, 并且经检验符合LR船级社规范的要求。 We hereby certify, that the material has been made by an approved process and satisfactorily tested in accordance with the Rules of Lloyd's Register.</p>	<p>B0A03=PERCENTAGE ELONGATION AFTER FRACTURE A0C01=IMPACT TEST A A0C012=IMPACT TEST B A0C013=IMPACT TEST C A0C02=IMPACT AVERAGE</p>	<p>冶金技术处处长 DIRECTOR OF METALLURGICAL DEPARTMENT</p> <p>野牛 YENIU</p>	<p>验船师 SURVEYOR</p> <p>S.J. He Dalian Office Lloyd's Register Classification Society China Co Ltd</p>
--	--	---	---